



PACIFIC EARTHQUAKE ENGINEERING RESEARCH CENTER

Effect of hoop reinforcement spacing on the cyclic response of large reinforced concrete special moment frame beams

**Marios Panagiotou
Tea Visnjic
Grigorios Antonellis
Panagiotis Galanis
Jack P. Moehle**

Department of Civil and Environmental Engineering
University of California, Berkeley

Disclaimer

The opinions, findings, and conclusions or recommendations expressed in this publication are those of the author(s) and do not necessarily reflect the views of the study sponsor(s) or the Pacific Earthquake Engineering Research Center.

Effect of hoop reinforcement spacing on the cyclic response of large reinforced concrete special moment frame beams

**Marios Panagiotou
Tea Visnjic
Grigorios Antonellis
Panagiotis Galanis
Jack P. Moehle**

Department of Civil and Environmental Engineering
University of California, Berkeley

PEER Report 2013/16
Pacific Earthquake Engineering Research Center
Headquarters at the University of California

June 2013

ABSTRACT

Recent developments in the construction of high-rise buildings in the highly seismic regions of the United States have resulted in construction of reinforced concrete special moment frame beams that are larger compared to those used previously. Governing building code requirements (ACI 318-08) for these beams were introduced in ACI 318-83 and are based on prevailing practices and technical knowledge from that period. When the existing provisions are applied to the larger beams that are now prevalent, hoop spacing can be as large as 305 mm (12 in.) in the beam plastic-hinge zone. An experimental study was conducted to explore the effectiveness of the ACI 318-08 provisions and to identify needed changes for ACI 318-11. Two large special moment frame beams were constructed and tested. The beams were 1219 mm (48 in.) deep by 762 mm (30 in.) wide, and constructed of normal-weight aggregate concrete having target compressive strength of 34 MPa (5000 psi). Longitudinal reinforcement consisted of five No. 36 (11) ASTM A706 Grade 60 bars at top and bottom faces. Transverse reinforcement consisted of No. 16 (5) hoops, where each hoop set was made up of a stirrup closed by a crosstie with an additional vertically oriented crosstie. Center-to-center spacing of hoop sets was either 279 mm (11 in.) or 152 mm (6 in.). The beams were subjected statically to cyclic displacement reversals to simulate effects of earthquake-induced deformations.

ACKNOWLEDGMENTS

We are grateful for financial support and in-kind contributions from Pankow Foundation, Webcor Builders, ACI Foundation's Concrete Research Council, and the CRSI Foundation, which provided the capability for constructing the test specimens and conducting the laboratory study. The work was conducted under the auspices of the Pacific Earthquake Engineering Research Center, using the laboratory test facilities of the Department of Civil and Environmental Engineering of the University of California, Berkeley.

The study arose from a concern by Robert Englekirk (Englekirk Structural Engineers) conveyed in a letter and a technical presentation to representatives of the American Concrete Institute (ACI). The Institute responded by promoting and partially sponsoring the development of the test program reported here, as well as an ACI 318 Code Change proposal that resulted in modifications of the Building Code Requirements for Structural Concrete [ACI 318-11 2011].

The study was guided by Robert Tener, Executive Director of Pankow Foundation, and by an expert Industry Advisory Committee comprising: Robert Englekirk (Englekirk Structural Engineers); Ron Klemencic (Magnusson Klemencic Associates); Joseph Maffei (Rutherford + Chekene); Mehran Pourzanjani (Saiful Bouquet Structural Engineers); Mark Sarkisian (Skidmore, Owings & Merrill LLP); and James Wight (University of Michigan). Ron Klemencic served as “Industry Champion” for the project in accordance with established practices for projects funded by the Pankow Foundation. These individuals had a very positive influence in directing the project work toward results that will affect industry and are readily usable.

Subcommittee H (Seismic) of the ACI’s Committee 318 (Building Code) reviewed results of the test program and worked with the authors to craft the building code language recommended in this report and later adopted as part of ACI 318-11. The close collaboration among funding agencies, expert practitioners, building code committee, and project participants streamlined the development and adoption of the building code provisions.

The authors thank Mr. Ross Yamamoto and Mr. James Sonu, undergraduate students in the Department of Civil and Environmental Engineering, University of California, Berkeley, for their work on data reduction as well as on developing the figures presented in Appendix A.

The opinions, findings, conclusions, and recommendations expressed in this publication are those of the authors and do not necessarily reflect the views of the study sponsors or the Pacific Earthquake Engineering Research Center.

CONTENTS

ABSTRACT.....	iii
ACKNOWLEDGMENTS	v
TABLE OF CONTENTS	vii
LIST OF TABLES AND FIGURES.....	ix
1 FINAL REPORT	1
1.1 Introduction.....	1
1.2 Test Specimens	3
1.3 Description of Materials Used in Construction.....	5
1.3.1 Concrete	5
1.3.2 Steel.....	6
1.4 Instrumentation.....	7
1.5 Test Protocol.....	10
1.6 Beam 1 Test: Response Overview and Observations.....	11
1.7 Beam 1 Test: Measured Local Response	16
1.8 Beam 2 Test Response Overview and Observations.....	20
1.9 Beam 2 Test: Measured Local Response	27
1.10 Comparison of Moment-Deformation Relations.....	30
1.11 Estimated Shear Deformations.....	31
1.12 Buckling Behavior of Longitudinal Reinforcement.....	32
1.13 Comparison of Measured and Calculated Flexural Response.....	34
1.14 Residual Crack Widths.....	37
1.15 Design Recommendation	38
1.16 Summary and Conclusions	40
REFERENCES	43
APPENDIX A: RECORDED INSTRUMENTATION DATA HISTORIES	45
APPENDIX B: FLEXURAL RESPONSE CALCULATIONS	63
APPENDIX C: RECORDED CRACK WIDTHS.....	87

LIST OF TABLES AND FIGURES

Table 1	28-day, 60-day, and 86-day concrete compressive strengths.	6
Table 2	Displacement test protocol (25.4 mm = 1 in.).	10
Figure 1	(a) Side view of the two beams; (b) plan view of the two beams; and (c) beam reinforcement details (25.4 mm = 1 in.).	4
Figure 2	Cross sections of Beams 1 and 2 including reinforcing steel details. (25.4 mm = 1 in.).	5
Figure 3	Compressive stress-strain relationship of cylinders: (a) test day of Beam 1 (60 days); and (b) test day of Beam 2 (86 days). (1 ksi = 6.895 MPa, 1 in. = 25.4 mm).	6
Figure 4	Tension stress-strain relationship of steel coupon tests: (a) No. 16 (5) bars used for the stirrups; and (b) No. 36 (11) bars used for the longitudinal reinforcement. (25.4 mm = 1 in., 1 ksi = 6.895 MPa).	7
Figure 5	Layout of displacement transducers: (a) plan view of top face of the beams; (b) plan view of bottom face of the beams; and (c) elevation view of side face of the beams (25.4 mm = 1 in.).	8
Figure 6	Layout of strain gauges attached on the longitudinal and transverse reinforcement of Beams 1 and 2: (a) location of instrumented hoops; (b) instrumented longitudinal bars; location of gauges attached on longitudinal bars: (c) type A, and (d) type B. Location of strain gauges on stirrups: (e) type C stirrup, and (f) type D stirrup (25.4 mm = 1 in.).	9
Figure 7	Beam 1: relation between maximum beam moment and drift ratio; (a) all cycles; and (b) cycles up to and including a drift ratio of 2.7% (1 kN-m = 0.737 kip-ft).	12
Figure 8	Beam 1: damage state at the beginning of cycle in which buckling occurred (first cycle with peak drift ratio = 2.7%, instantaneous drift ratio = -0.9%).	13
Figure 9	Beam 1: buckling of the top longitudinal bars (first cycle with peak drift ratio = 2.7%, instantaneous drift ratio = -2.7%).	13
Figure 10	Beam 1: buckling of the top longitudinal bars (first cycle with peak drift ratio = 2.7%, instantaneous drift ratio = 2.7%).	14
Figure 11	Beam 1: Top view of damage state (first cycle with peak drift ratio = 2.7%, instantaneous drift ratio = 2.7%).	14
Figure 12	Beam 1: overview after the buckling of the top longitudinal bars (first cycle with peak drift ratio = 2.7%, instantaneous drift ratio = -2.7%).	15
Figure 13	Beam 1: overview at the maximum positive displacement (cycle with peak drift ratio = 5.5%, instantaneous drift ratio = 5.5%).	15

Figure 14	Beam 1: overview at the maximum negative displacement (cycle with peak drift ratio= -5.5%, instantaneous drift ratio= -5.5%).	16
Figure 15	Beam 1: profiles of elongation measured between steel instrumentation rods normalized to gauge length. Note: negative elongation corresponds to shortening.	18
Figure 16	Beam 1: histories of elongation measured between steel instrumentation rods normalized to gauge length. Response only up to peak drift ratio of 2.7% is shown.	18
Figure 17	Beam 1: histories of strain measured using LVDTs and strain gauges: (a) top face; (b) bottom face; (c) side face; and (d) side face. Characteristic instants of peak drift ratios are shown in the x-axis.	19
Figure 18	Beam 1: strains measured with gauges on steel reinforcement 51 mm (2 in.) from the face of the beam (top and bottom of the reinforcing bar); (a) presented as strain versus drift ratio; and (b) history of strains.	19
Figure 19	Beam 1: drift ratio due to fixed-end rotation versus total drift ratio.	20
Figure 20	Beam 2: relation between maximum beam moment and beam drift ratio; (a) all cycles; and (b) cycles up to and including a drift ratio of 3.9% (1 kN-m = 0.737 kip-ft).	21
Figure 21	Beam 2: damage state during the second cycle with a peak drift ratio of 2.9% (instantaneous drift ratio = -2.0%).	22
Figure 22	Beam 2: damage state during the second cycle with a peak drift ratio of 2.9% (instantaneous drift ratio = -2.9%).	22
Figure 23	Beam 2: top view of damage state (first cycle with peak drift ratio = 2.9%, instantaneous drift ratio = -0.6%).	23
Figure 24	Beam 2: top view of damage state (first cycle with peak drift ratio = 2.9%, instantaneous drift ratio = -2.9%).	23
Figure 25	Beam 2: buckling of the top longitudinal reinforcement (first cycle with peak drift ratio = 3.9%, instantaneous drift ratio = -3.9%).	24
Figure 26	Beam 2: damage state at the beginning of the displacement cycle in which bottom longitudinal reinforcement buckled (maximum drift ratio = 5.3 %, instantaneous drift ratio = 0.8%).	24
Figure 27	Beam 2: buckling of bottom longitudinal reinforcement (instantaneous drift ratio equal to peak cycle drift ratio of 5.3%).	25
Figure 28	Beam 2: rupture of a top longitudinal bar (instantaneous drift ratio = 0.7 %, peak cycle drift ratio = 5.8 %).	25
Figure 29	Beam 2: overview at the instant of top reinforcement buckling (first cycle with peak drift ratio = 3.9%, instantaneous drift ratio = -3.9%).	26
Figure 30	Beam 2: overview at the maximum positive displacement (drift ratio = 5.8%).	26

Figure 31	Beam 2: overview at the maximum negative displacement (drift ratio = - 6.4%).	27
Figure 32	Beam 2: profiles of elongation measured between steel instrumentation rods normalized to gauge length. Note: negative elongation corresponds to shortening.	28
Figure 33	Beam 2: histories of elongation measured between steel instrumentation rods normalized to gauge length.	29
Figure 34	Beam 2: strain histories measured with strain gauges or displacement transducers at different locations of the beam.	30
Figure 35	Beam 2: drift due to fixed-end rotation versus total drift ratio.	30
Figure 36	Relation between beam moment and beam drift ratio for Beams 1 and 2.	31
Figure 37	Relation between measured force and estimated shear deformations for Beams 1 and 2 and cycles preceding the bar buckling.	32
Figure 38	Cyclic stress strain of steel and definition of characteristics strains.	33
Figure 39	Strain range ϵ_p as function of L_b / d_b (taken as being equivalent to s_h / d_b) [after Rodriguez et al. (1999)].	34
Figure 40	Comparison of calculated response envelopes and the measured response of Beam 1.	36
Figure 41	Comparison of calculated response envelopes and the measured response of Beam 2.	37
Figure 42	Beam 2: residual crack width as function of peak drift ratio.	38
Figure A.1	Beam 1: histories of displacement transducers.	47
Figure A.2	Beam 1: histories of displacement transducers.	48
Figure A.3	Beam 1: histories of displacement transducers.	49
Figure A.4	Beam 1: histories of strain gauges.	50
Figure A.5	Beam 1: histories of strain gauges.	51
Figure A.6	Beam 1: histories of strain gauges.	52
Figure A.7	Beam 1: histories of strain gauges.	53
Figure A.8	Beam 1: histories of displacement transducers.	54
Figure A.9	Beam 2: histories of displacement transducers.	55
Figure A.10	Beam 2: histories of displacement transducers.	56
Figure A.11	Beam 2: histories of strain gauges.	57
Figure A.12	Beam 2: histories of strain gauges.	58
Figure A.13	Beam 2: histories of strain gauges.	59
Figure A.14	Beams 2: histories of strain gauges.	60
Figure A.15	Beam 2: histories of strain gauges.	61

1 Final Report

1.1 INTRODUCTION

Construction of tall buildings is increasing in earthquake-prone regions of the United States (U.S.) and around the world. Reinforced concrete special moment resisting frames (referred to as “special moment frames” in ACI 318 [2011] and sometimes abbreviated to SMRFs) are commonly selected as the seismic force-resisting system in such buildings. In taller buildings, SMRF beams with height as deep as 1219 mm (48 in.) are not uncommon. In the U.S., reinforced concrete SMRFs are generally designed and detailed in accordance with ACI 318 [ACI 2008]. The ACI 318 provisions are structured around the strong column-weak beam philosophy, whereby the majority of inelastic flexural deformations are designed to occur in the columns at the bottom of the first story and in the beams along the height of the building. Therefore, it is important that SMRF beams be capable of stable inelastic flexural response at deformation levels consistent with the building code design provisions.

The numerical seismic response of tall reinforced concrete SMRFs designed according to ACI 318 provisions has been studied by Haselton et al. [2008] and Visnjic et al. [2012]. Visnjic et al. [2012] reported 2% and 3% mean interstory drift ratios in generic 20-story tall SMRFs located in Los Angeles, California, at design basis earthquake (DBE) and maximum considered earthquake (MCE) levels of shaking, respectively. Although the exact relationship between interstory drift ratio and beam chord rotation depends on the geometry of the framing system and varies continuously during earthquake shaking, typically the beam rotation is found to be approximately equal to the interstory drift ratio. For example, for the frames reported in Visnjic et al. [2012], beam rotations are about 1.3 times the interstory drift ratios, resulting in mean beam rotations of 0.026 and 0.039 at the DBE and the MCE hazard levels, respectively. According to that study, more than 30% of the beams along the height of the frame may reach this rotation amplitude.

Few experimental studies of reinforced concrete beams or beam-column subassemblies have been carried out with beam depth h greater than 610 mm (24 in.). For example, in Popov et al. [1972] $h = 737$ mm (29 in.); Blakeley et al. [1975,] $h = 889$ mm (35 in.); Birss [1978] $h = 610$ mm (24 in.); Beckingsale [1980] $h = 610$ mm (24 in.); Restrepo et al. [1990] $h = 700$ mm (27.5 in.); Warcholik and Priestley [1997] $h = 737$ mm (29 in.); and Chang et al. [2008] $h = 914$ mm (36 in.). These studies have shown that the degree of damage at different amplitudes of deformation depends primarily on the amount of longitudinal reinforcement; the shear span ratio (defined as the moment at the beam end divided by the product of the shear force and the beam height); and the quantity, spacing, configuration, and material properties of the transverse reinforcement. Predominant modes of failure of flexure-dominated beams under cyclic loading

include moderate inelastic response of the transverse reinforcement and diagonal cracking resulting in stiffness degradation, bond degradation of the longitudinal reinforcement, and buckling of the longitudinal reinforcement.

Among the three beam tests reported in Popov et al. [1972], only one (beam 43) would satisfy ACI 318-08's shear strength requirements. This beam had longitudinal tension reinforcement ratio $\rho = A_s/bd = 1.58\%$ (A_s = area of tension reinforcement, b = beam width, and d = distance from extreme compression fiber to centroid of longitudinal reinforcement), longitudinal compression reinforcement ratio $\rho' = 1.58\%$, and ratio of hoop spacing to longitudinal bar diameter $s_h / d_b = 2.66$. It sustained seven cycles of increasing displacement amplitude and 4.5% peak drift ratio (defined as the lateral displacement of the beam divided by the beam length) before significant stiffness degradation due to inelastic strains of the stirrups and major diagonal cracking occurred. Beams tested by Blakeley et al. [1975], as part of beam-column subassemblies, with $\rho = 1.1\%$ and 1.03% , $\rho' = 0.7\%$, $s_h / d_b = 5.3$, and yield strength of steel $f_y = 300$ MPa (44 ksi), sustained cycles of increasing displacement amplitude to more than 5% peak drift ratio before significant stiffness degradation occurred due to bar buckling and diagonal cracking. The transverse reinforcement of these beams consisted of two No. 16 (5) hoops with 127 mm (5 in.) long hooks. Beams 5 and 6 tested by Restrepo et al. [1990], with $\rho = 0.93\%$ and $s_h / d_b = 4.2$, sustained five and six cycles, respectively, of increasing displacement amplitude and a peak drift ratio of 3.6% before major stiffness degradation occurred due to bond failure of the longitudinal reinforcement and crushing of the corresponding cover concrete in one of the beams; major diagonal cracking and shear deformations occurred in the other. No major buckling of the longitudinal reinforcement occurred in any of the beams described above. Two out of the four beams tested by Chang et al. [2008] had a rectangular section shape, used ductile threaded rods for longitudinal reinforcement with $\rho = 0.6\%$, had transverse reinforcement layout with $s_h / d_b = 1.5$, and used normal- and high-strength concrete. Both beams sustained more than 5.5% peak drift ratio before major stiffness degradation occurred. No major buckling of the longitudinal reinforcement was observed up to this level of response.

According to ACI 318-08, design shear strength is the shear corresponding to development of probable flexural strength, M_{pr} , acting at beam ends concurrent with design gravity loads. Within a length $2h$ from the end of a SMRF beam end, hoops must be designed to resist the entire shear (the concrete contribution is ignored). A hoop may consist of a single piece of reinforcement, or it may consist of a stirrup closed at the top by a crosstie. To improve lateral support for the longitudinal reinforcement, ACI 318 also requires that at least the corner and alternate bars must have lateral support provided by the corner of a tie or crossties, with no unsupported bar more than 152 mm (6 in.) clear from a supported bar. Furthermore, Section 21.5.3.2 requires that hoop spacing, s_h , within $2h$ of the beam ends shall not exceed the least of $d / 4$, $8d_b$, $24d_{bh}$, and 305 mm (12 in.), where d_{bh} is the hoop-bar diameter. The amount and configuration of the hoops determines not only the shear strength of a beam but also its resistance against buckling of the longitudinal reinforcement, which has been shown by Monti and Nuti [1992] and Rodriguez et al. [1999] to depend strongly on s_h / d_b .

The study reported herein investigates the experimental static cyclic response of two 1219-mm- (48-in.-) deep \times 762-mm- (30-in.-) wide reinforced concrete beams designed

according to ACI 318-08. These are believed to be the largest SMRF beams to have been tested under simulated seismic loading in a laboratory. The beams had longitudinal tension reinforcement consisting of five No. 36 (11) ASTM A706 bars corresponding to $\rho = 0.58\%$. The beams had No. 16 (5) hoops having longitudinal spacing of 279 mm (11 in.) in one beam and 152 mm (6 in.) in the other beam, corresponding to s_h / d_b equal to 7.8 and 4.3, respectively. The specified concrete compressive strength in both beams was 34 MPa (5000 psi).

1.2 TEST SPECIMENS

Two test beams were designed and constructed to test the ACI 318-08 Building Code provisions and proposed code changes. The beams cantilevered from a common reaction block that was anchored to the laboratory floor; see Figure 1 (refer to Figure 12 and Figure 29 for test fixture photos). The beams were tested by imposing displacement cycles (upward and downward) to simulate the effects of deformation reversals that occur during a major earthquake. Positive displacement and force values correspond to downward displacement imposed 3810 mm (150 in.) from the interface of the beam with the anchorage block.

Beam 1 [Figure 2(a)] was designed to satisfy all provisions for special moment frame beams according to ACI 318-08. The beam hoops [No. 16 (5) at spacing $s_h = 279$ mm (11 in.)] were each made up of three pieces: a stirrup with seismic hooks, a crosstie at the top to close the hoop, and an additional vertical crosstie to restrain longitudinal bars along the top and bottom faces. The crossties were alternated end-for-end along the length of the beam. The volumetric confinement reinforcement ratio was $\rho'' = 0.31\%$, where $\rho'' = \text{volume of vertical legs of hoops} / \text{volume of the concrete core}$. This corresponds to a nominal confinement pressure $\rho'' f_{yt} = 0.038 f'_c$, where $f_{yt} = 413$ MPa (60 ksi) is the specified yield stress of the steel used for the transverse reinforcement and $f'_c = 34$ MPa (5 ksi) is the specified compressive strength of concrete. In Beam 2 [Figure 2(b)], the hoop spacing s_h was reduced to 152 mm (6 in.), corresponding to a volumetric reinforcement ratio $\rho'' = 0.57\%$ and nominal confinement pressure $0.068 f'_c$. Longitudinal reinforcement in both beams was identical.




Figure 2 Cross sections of Beams 1 and 2 including reinforcing steel details. (25.4 mm = 1 in.).

1.3 DESCRIPTION OF MATERIALS USED IN CONSTRUCTION

1.3.1 Concrete

Normal-weight concrete was used, with pea gravel (not crushed) as the maximum size aggregate, with target compressive strength of 34 MPa (5 ksi). A total of 19.6 cubic meters (25.6 cubic yards) of concrete was required for construction of the two beam specimens and the reaction block. Three batches of concrete were used; 18 standard 152 mm (6 in.) \times 305 mm (12 in.) cylinders were cast for material testing. The first batch was cast mainly on the bottom of the reaction block and a portion of the bottom part of both beams. The second batch was cast over the middle portion of the beams and the reaction block, and the third batch topped off the remaining part of the block and the beams. Table 1 summarizes the compressive strength results obtained at 28, 60, and 86 days after casting for each of the three concrete batches. The last two tests were conducted on the days the experiments took place for Beams 1 and 2, respectively.

The 28-day strength test included 9 cylinders, three for each batch. Compressive strengths for the three batches ranged from 36.0 to 38.4 MPa (5.23 to 5.58 ksi), with average of 36.8 MPa (5.34 ksi).

Testing of the first beam took place 60 days after casting the beams and cylinders, at which time two cylinders were tested for each concrete batch. Their corresponding stress-strain relations are plotted in Figure 3. The labeling convention for each curve is "mNo. - No.", where "mNo." signifies batch number, and "-No." signifies specimen number. For example, "m2-1" stands for specimen 1 of batch number 2. Average compressive strength calculated for the six cylinders was $f'_c = 40.0$ MPa (5.8 ksi), and the average strain at maximum compressive strength was calculated to be $\epsilon_o = 0.3\%$.

Testing of the second beam took place 86 days after casting and the remaining three cylinders were tested on this day (one for each concrete batch). The stress-strain curves for these

three specimens are plotted in Figure 3. The calculated average compressive strength was $f'_c = 42.3$ MPa (6.1ksi). Again, the average strain at maximum compressive strength was $\epsilon_o = 0.3\%$.

Table 1 28-day, 60-day, and 86-day concrete compressive strengths.

Concrete Age	Batch	Compressive strength of concrete f'_c , MPa (ksi)				Average
		Specimen 1	Specimen 2	Specimen 3	Average	
28 days	1	37.3 (5.41)	35.5 (5.15)	35.7 (5.17)	36.1 (5.24)	36.8 (5.34)
	2	36.3 (5.27)	36.2 (5.25)	35.6 (5.17)	36.0 (5.23)	
	3	38.6 (5.60)	39.0 (5.66)	37.7 (5.48)	38.4 (5.58)	
60 days	1	39.2 (5.69)	39.1 (5.68)	-	39.2 (5.69)	40.1 (5.82)
	2	38.3 (5.55)	39.0 (5.66)	-	38.6 (5.61)	
	3	41.9 (6.09)	43.1 (6.26)	-	42.5 (6.17)	
86 days	1	40.7 (5.91)	-	-	40.7 (5.91)	42.3 (6.13)
	2	40.4 (5.87)	-	-	40.4 (5.87)	
	3	45.8 (6.65)	-	-	45.8 (6.65)	

Note: Beam 1 was tested at concrete age of 60 days. Beam 2 was tested at concrete age of 86 days.




Figure 3 Compressive stress-strain relationship of cylinders: (a) test day of Beam 1 (60 days); and (b) test day of Beam 2 (86 days). (1 ksi = 6.895 MPa, 1 in. = 25.4 mm).

1.3.2 Steel

The longitudinal reinforcement consisted of five No. 36 (11) bars at the top and bottom of the beam. The transverse reinforcement consisted of No. 16 (5) reinforcing bars. Type ASTM A706

Grade 60 steel was used for both the longitudinal and transverse reinforcement. Three steel deformed bars were tested for each of the two reinforcement sizes. Figure 4 plots the measured stress-strain relations. As can be seen in Figure 4(a), the No. 16 (5) reinforcement did not display a yield plateau. The average yield stress was $f_y = 455$ MPa (66 ksi). The three coupons reached an average maximum stress of $f_u = 710$ MPa (103 ksi).

For the No. 11 longitudinal bars, the average yield stress was $f_y = 503$ MPa (73 ksi). A well-defined yield plateau developed for all three specimens, with the average strain at the onset of strain hardening equal to $\epsilon_{sh} = 1.2\%$ [Figure 4(b)]. Maximum measured stress in steel had an average of $f_u = 723$ MPa (105 ksi).




Figure 4 Tension stress-strain relationship of steel coupon tests: (a) No. 16 (5) bars used for the stirrups; and (b) No. 36 (11) bars used for the longitudinal reinforcement. (25.4 mm = 1 in., 1 ksi = 6.895 MPa).

1.4 INSTRUMENTATION

The instrumentation of the test specimens included displacement transducers [linear variable differential transformers (LVDTs)] connected between steel rods attached to the concrete, which extended through the cover and approximately 40 mm (1.5 in.) into the concrete core at the top, side, and bottom faces of the specimen. Strain gauges were attached to the reinforcing steel at selected locations. In addition, displacement transducers were placed between the bottom face of the beam and the strong floor at the point where the load was applied. Figure 5 shows a plan view of the displacement transducers at the top and bottom faces of the beam, as well as an elevation view of the transducers attached along the side face of the beams. Two rows of displacement transducers were placed along the top face (TL, TR series) and bottom face (BL, BR series) of each beam. Figure 6 depicts the location of the gauges, and the longitudinal bars and stirrups that were instrumented with strain gauges.





Figure 5 Layout of displacement transducers: (a) plan view of top face of the beams; (b) plan view of bottom face of the beams; and (c) elevation view of side face of the beams (25.4 mm = 1 in.).



1.5 TEST PROTOCOL

The displacement test protocol of Beams 1 and 2 is described below. Table 2 lists the displacement amplitude Δ (measured with a displacement transducer connected between the bottom face of the beam and the strong floor), the number of cycles at each displacement amplitude, the equivalent drift ratio Θ (defined as Δ / L , where L = distance from face of anchorage block to point where load was applied and Δ was measured), and the displacement ductility $\mu_{\Delta} = \Delta / \Delta_y$, where Δ_y is the yield displacement. The yield displacement was calculated as $\Delta_y = \phi_y L^2 / 3 + \Delta_{sp}$, where ϕ_y = calculated yield curvature = 2.55×10^{-6} rad/mm, and Δ_{sp} = calculated displacement due to strain penetration at the anchorage block = 5 mm. Yield curvature, which is defined as the curvature corresponding to first yielding of the longitudinal reinforcement, was calculated with moment curvature analysis assuming linear variation of strain through the beam depth. For the values described above $\Delta_y = 18$ mm (0.7 in.). As shown in Table 2, for step 16 of Beam 2 the peak positive and negative displacement were different with the negative indicated in parenthesis.

Table 2 Displacement test protocol (25.4 mm = 1 in.).

Step	Displacement Δ (mm)		Number of cycles	Drift ratio $\Theta = \Delta / L * 100$		Displacement ductility $\mu_{\Delta} = \Delta / \Delta_y$	
	Beam 1	Beam 2		Beam 1	Beam 2	Beam 1	Beam 2
1	3	3	3	0.07	0.07	0.2	0.2
2	7	6	3	0.18	0.16	0.4	0.3
3	11	11	3	0.28	0.28	0.6	0.6
4	14	15	3	0.38	0.40	0.8	0.9
5	31	33	3	0.81	0.87	1.7	1.9
6	46	46	2	1.2	1.2	2.6	2.6
7	13	13	1	0.33	0.33	0.7	0.7
8	69	69	2	1.8	1.8	3.9	3.9
9	13	13	1	0.33	0.33	0.7	0.7
10	103	109	2	2.7	2.9	5.8	6.2
11	13	13	1	0.33	0.33	0.7	0.7
12	139	147	2	3.6	3.9	7.8	8.3
13	13	13	1	0.33	0.33	0.7	0.7
14	194	203	1	5.1	5.3	10.9	11.4
15	13	13	1	0.33	0.33	0.7	0.7
16	210	222 (-244)	1	5.5	5.8 (-6.4)	11.8	12.5 (-13.7)

1.6 BEAM 1 TEST: RESPONSE OVERVIEW AND OBSERVATIONS

This section presents the main observations from the test of Beam 1 designed according to the ACI 318-08 provisions, with No. 16 (5) hoops at 279 mm (11 in.) spacing. Figure 7(a) shows the measured relations between resisting beam moment and beam drift ratio Θ for all the cycles. Figure 7(b) shows the response up to the peak drift ratio up to 2.7%, where strength degradation due to buckling of the longitudinal reinforcement was observed. The reported moment is the sum of moments due to actuator force and beam self-weight, assuming a self-weight of the beam equal to 90.1 kN (20.3 kips). The initial deflection due to self-weight of the beam is negligible and is not accounted for in the reported drift values.

Figure 7 shows the calculated probable flexural strength, $M_{pr} = 2870$ kN-m (2110 kip-ft), calculated in accordance with Chapter 21 of ACI 318-08. As required by ACI 318, M_{pr} is calculated for nominal (specified) concrete compressive strength of 34 MPa (5000 psi) and elasto-plastic steel stress-strain relation with yield stress taken equal to 1.25 times specified yield stress [that is, $1.25 \times 414 \text{ MPa} = 517 \text{ MPa}$ (75 ksi)]. Skin reinforcement is not included in the strength calculation because the skin reinforcement is not fully developed into the anchor block [Figure 1(c)]. Consideration of the skin reinforcement, if assumed fully developed into the anchor block, would result in a 9% increase in M_{pr} . The peak measured moment was equal to 2850 kN-m (2100 kip-ft), which is very close to the calculated M_{pr} .

The test specimen developed cracks primarily perpendicular to the longitudinal axis (attributable to moment) and cracks inclined to the longitudinal axis (attributable to shear), see Figure 8. The peak shear force of 739 kN (164 kips) corresponds to a nominal shear stress of 0.83 MPa (121 psi), or $0.13\sqrt{f'_c}$ MPa ($1.6\sqrt{f'_c}$ psi) using measured compressive strength. According to ACI, for beams of special moment frames, the nominal shear strength within the twice the member thickness from the column face (that is, the intended plastic hinge zone) is calculated assuming no contribution from concrete, that is, with $V_c = 0$. Thus, using the specified material properties, the nominal shear strength for this beam is $V_n = V_s = A_v f_{yt} d/s = 1020$ kN (229 kips). If the shear strength is defined as $V_n = V_c + V_s$, where $V_c = 0.17\sqrt{f'_c} b_w d$, MPa ($2\sqrt{f'_c} b_w d$, psi), then the calculated nominal shear strength is $V_n = 1870$ kN (421 kips). As shown in Figure 8, visible movement along steeply inclined cracks resulted in horizontal cracks along the longitudinal reinforcement (initially attributable to dowel action, but possibly also influenced by bond stress and initiation of longitudinal bar buckling).

The test specimen sustained the first half cycle to 2.7% drift ratio without evident failure. Upon deformation reversal during the second half cycle, however, all the top longitudinal bars buckled extensively, creating a “crack cave” that remained open for all the remaining cycles (Figure 9). During the second cycle with a peak drift ratio of 2.7%, the maximum resistance of the beam reduced by 30% (Figure 7). For the next two cycles with drift ratio amplitudes 3.6% and 5.1%, the resistance of the beam reduced to 50% of the peak resistance. As explained subsequently in the section on measured local response, buckling also occurred at the bottom of the beam during cycle with 2.7% peak drift ratio. Bulging of the bottom face of the beam is visible in Figure 10.




Figure 7 Beam 1: relation between maximum beam moment and drift ratio; (a) all cycles; and (b) cycles up to and including a drift ratio of 2.7% (1 kN-m = 0.737 kip-ft).

Figure 11 shows the crack pattern at the top of the beam for downward displacement of the beam. Wide cracks developed from the fixed end along a length of the beam equal to approximately half the beam depth. These major cracks were about 250 mm (10 in.) apart, which is close to the hoop spacing [279 mm (11 in.)] of this beam. After longitudinal reinforcement buckling occurred, shearing deformations contributed significantly to the total beam displacement and were especially notable for downward displacement (Figure 12 through Figure 14).



Figure 8

Beam 1: damage state at the beginning of cycle in which buckling occurred (first cycle with peak drift ratio = 2.7%, instantaneous drift ratio = -0.9%).



Figure 9

Beam 1: buckling of the top longitudinal bars (first cycle with peak drift ratio = 2.7%, instantaneous drift ratio = -2.7%).



Figure 10 Beam 1: buckling of the top longitudinal bars (first cycle with peak drift ratio = 2.7%, instantaneous drift ratio = 2.7%).




Figure 11 Beam 1: Top view of damage state (first cycle with peak drift ratio = 2.7%, instantaneous drift ratio = 2.7%).



Figure 12 Beam 1: overview after the buckling of the top longitudinal bars (first cycle with peak drift ratio = 2.7%, instantaneous drift ratio = -2.7%).



Figure 13 Beam 1: overview at the maximum positive displacement (cycle with peak drift ratio = 5.5%, instantaneous drift ratio = 5.5%).



Figure 14 **Beam 1: overview at the maximum negative displacement (cycle with peak drift ratio= -5.5%, instantaneous drift ratio= -5.5%).**

1.7 BEAM 1 TEST: MEASURED LOCAL RESPONSE

Measured local responses include reinforcement strains, slip of reinforcement from the anchorage block due to strain penetration, and local deformations along the top, bottom, and side faces of the beams. Strains were measured by electrical resistance strain gauges attached to reinforcement; LVDTs were connected to steel instrumentation rods that were anchored into the concrete, enabling measurement of deformations between fixed points. Initially, measurements from these LVDTs were used to estimate average longitudinal strains, defined as the elongation measured by an LVDT divided by its gauge length. After buckling of longitudinal reinforcement initiated, however, distortion of the concrete cover resulted in displacement and rotation of the steel instrumentation rods, such that the resulting measurement no longer represented the average strain correctly. Nonetheless, these instruments proved valuable in identifying the onset and extent of buckling. For all reported strain measures, positive strain indicates elongation.

The response of this beam during later stages of testing was characterized by extensive buckling of the longitudinal reinforcement that initiated during the cycles with 1.8% peak drift ratio and became more extensive during the cycles with 2.7% peak drift ratio. The onset of buckling can be identified by examining the data from the LVDTs spanning across steel instrumentation rods attached to the top and bottom faces of the beam. Figure 15 plots the LVDT readings, normalized to their respective gauge lengths, for peak displacement amplitudes during various displacement cycles. For LVDTs attached to the top face (TL series and TR series), data are presented for upward displacement peaks, while for LVDTs attached to the bottom face (BL series and BR series), data are presented for downward displacement peaks. Along the top face, the data show an “elongation bulge” associated with buckling of the top longitudinal reinforcement, which becomes apparent for the 1.8% drift cycles, and is centered around 500

mm (20 in.) from the beam end. Along the bottom face, the data show a similar bulge associated with buckling of the bottom longitudinal reinforcement, which initiated during the cycles with 1.8% peak drift ratio and became more noticeable for the 2.7% drift cycles, and is centered around 381 mm (15 in.) from the beam end.

Figure 16 plots the histories of two LVDTs spanning the center of the buckling region for the top and bottom of the beam. It is noteworthy that the deformation measurements indicate that only tensile strains develop throughout the history. Apparently, cracks that open under flexural tension never fully close under flexural compression. For loading in the direction that would tend to result in flexural compression, the gauges indicate partial crack closure (due to compression) except for the cycle in which significant buckling occurs, for which case the outward buckle results in a tensile reading of the displacement gauge.

Strains were measured with strain gauges attached on the longitudinal and transverse reinforcement. Figure 17 compares strain histories inferred from the displacement transducers and those “measured” by the strain gauges for select gauges. Figure 17(a) and (b) show similar trends in peak tensile strains, although values differed notably during some portions of the history. The average vertical strains of the side face of the beam, measured with LVDTs (Figure 5), are shown in Figure 17(c). The readings suggest transverse strains exceeding 0.2%, corresponding to the yield strain for the transverse reinforcement. Figure 17(d) shows strains up to 0.35% were measured using strain gauges attached to the stirrups, suggesting that stirrup yielding may have occurred. The majority of these strain gauges failed after measuring a strain around 2%, such that strains were not recorded during the largest displacement cycles, including those for which buckling was observed.

Figure 18 depicts the strain histories of a top longitudinal bar at 51 mm (2 in.) from the fixed end of the beam. Note that strain gauges were located at both the top surface and the bottom surface of the bar at this location. For the cycles with a peak drift ratio up to 2.7%, similar peak strains were measured on the top surface (Gauge LTI-OUT1, Figure 6) and the bottom surface (Gauge LTI-IN1, Figure 6) of the bar. After this drift ratio, where significant buckling initiated, the measured strains on top and bottom of the bar differed significantly, apparently because of curvature as the bar buckled. Note that at -5.1% drift ratio, the strain at the top and the bottom of the reinforcing bar was 5.9%, and -2%, respectively.

As shown in Figure 5, displacement transducer TL1 measured displacement of the “fixed end” of the beam relative to the anchorage block. In effect, this instrument measured slip of the longitudinal reinforcement from the block. Figure 19 shows the measured slip versus drift ratio. The contribution of fixed-end rotation at the total drift ratio of the specimen was significant. For example, at 2.7% drift ratio the measured displacement of TL1 was 15.5 mm (0.6 in.). Assuming zero deformation at the bottom of the beam, this corresponds to a rotation angle of $15.5/1219 = 1.27\%$, or 47% of the total drift ratio.




Figure 15 Beam 1: profiles of elongation measured between steel instrumentation rods normalized to gauge length. Note: negative elongation corresponds to shortening.




Figure 16 Beam 1: histories of elongation measured between steel instrumentation rods normalized to gauge length. Response only up to peak drift ratio of 2.7% is shown.




Figure 17 Beam 1: histories of strain measured using LVDTs and strain gauges: (a) top face; (b) bottom face; (c) side face; and (d) side face. Characteristic instants of peak drift ratios are shown in the x-axis.




Figure 18 Beam 1: strains measured with gauges on steel reinforcement 51 mm (2 in.) from the face of the beam (top and bottom of the reinforcing bar); (a) presented as strain versus drift ratio; and (b) history of strains.




Figure 19 Beam 1: drift ratio due to fixed-end rotation versus total drift ratio.

1.8 BEAM 2 TEST RESPONSE OVERVIEW AND OBSERVATIONS

This section presents the main observations from the test of Beam 2, designed according to ACI 318-08 provisions, but with No. 16 (5) hoop spacing reduced to 152 mm (6 in.). Figure 20(a) and (b) illustrate the beam moment versus drift ratio response up to 6.4%, and 3.9% drift ratio, respectively. Significant longitudinal bar buckling initiated upon reversal from peak drift during the second cycle with 2.9% peak drift ratio. Bar buckling became excessive and obvious in the measured moment-drift response in the cycle with 3.9% peak drift ratio.

For this beam, the calculated value of M_{pr} is that same as that obtained for Beam 1 (because M_{pr} is based on nominal properties), resulting in $M_{pr} = 2870$ kN-m (2110 kip-ft). The measured maximum moment was $M_{max} = 3148$ kN-m, which is 10% greater than the M_{pr} . The peak measured shear force of 805 kN (181 kips) corresponds to a nominal shear stress of 0.90 MPa (133 psi), or $0.14\sqrt{f'_c}$ MPa ($1.7\sqrt{f'_c}$ psi) using measured compressive strength. Nominal shear strength calculated using specified material properties in accordance with ACI 318 is $V_n = V_s = A_v f_{yt} d/s = 1870$ kN (420 kips). Here, the assumption was that $V_c = 0$. If the strength is defined as $V_n = V_c + V_s$, with $V_c = 0.17\sqrt{f'_c} b_w d$, MPa ($2\sqrt{f'_c} b_w d$, psi), then calculated nominal shear strength is $V_n = 2720$ kN (612 kips). The behavior of Beam 2 was similar to Beam 1 in the early cycles, including development of cracks apparently associated with flexure, shear, and dowel action. Figure 21 shows the visible condition of the beam during the second cycle to 2.9% drift ratio.

During the second cycle to a drift ratio of 2.9%, as the beam drift was being reversed from positive drift to negative drift, horizontal cracks associated with initiation of bar buckling and top bar dowel action grew noticeably (see Figure 21 and Figure 22). Figure 23 shows the damage state, as viewed from the top, at the beginning of the negative half of this cycle. Figure 24 shows the same view but at the peak negative drift. Bulging of the top surface of the beam was noted due to buckling of the top reinforcement. Buckling of the top longitudinal reinforcement became more apparent during the following loading cycle to a peak drift ratio of 3.9%. As shown in Figure 25, compression zone crushing of concrete extended deep into the

beam at this time. The peak resistance of the beam after longitudinal bar buckling was 10% less than the maximum strength for this direction of loading.

Buckling of the bottom longitudinal bars became obvious during a cycle with a peak drift of 5.3% (Figure 26 and Figure 27).

During the last loading cycle, corresponding to a 5.8% peak positive drift ratio, one of the top corner bars fractured (Figure 28) at a beam drift ratio of 0.7%, resulting in a sudden strength loss in the beam of approximately 38%. The peak resistance for this cycle was 43% lower than for the previous downward cycle and 48% lower than the peak strength for loading in this direction. Figure 29 through Figure 31 show overall views of Beam 2 during large displacement cycles.




Figure 20 Beam 2: relation between maximum beam moment and beam drift ratio; (a) all cycles; and (b) cycles up to and including a drift ratio of 3.9% (1 kN-m = 0.737 kip-ft).



Figure 21 **Beam 2: damage state during the second cycle with a peak drift ratio of 2.9% (instantaneous drift ratio = -2.0%).**



Figure 22 **Beam 2: damage state during the second cycle with a peak drift ratio of 2.9% (instantaneous drift ratio = -2.9%).**




Figure 23 **Beam 2: top view of damage state (first cycle with peak drift ratio = 2.9%, instantaneous drift ratio = -0.6%).**



Figure 24 **Beam 2: top view of damage state (first cycle with peak drift ratio = 2.9%, instantaneous drift ratio = -2.9%).**



Figure 25 **Beam 2: buckling of the top longitudinal reinforcement (first cycle with peak drift ratio = 3.9%, instantaneous drift ratio = -3.9%).**



Figure 26 **Beam 2: damage state at the beginning of the displacement cycle in which bottom longitudinal reinforcement buckled (maximum drift ratio = 5.3 %, instantaneous drift ratio = 0.8%).**



Figure 27 Beam 2: buckling of bottom longitudinal reinforcement (instantaneous drift ratio equal to peak cycle drift ratio of 5.3%).




Figure 28 Beam 2: rupture of a top longitudinal bar (instantaneous drift ratio = 0.7 %, peak cycle drift ratio = 5.8 %).



Figure 29 **Beam 2: overview at the instant of top reinforcement buckling (first cycle with peak drift ratio = 3.9%, instantaneous drift ratio = -3.9%).**



Figure 30 **Beam 2: overview at the maximum positive displacement (drift ratio = 5.8%).**



Figure 31 **Beam 2: overview at the maximum negative displacement (drift ratio = -6.4%).**

1.9 BEAM 2 TEST: MEASURED LOCAL RESPONSE

As with Beam 1, the response of this beam during later stages of testing was characterized by extensive buckling of the longitudinal reinforcement. The onset of buckling can be identified by examining the data from the LVDTs spanning across steel instrumentation rods attached to the top and bottom faces of the beam. Figure 32 plots the LVDT readings, normalized to their respective gauge lengths, for peak displacement amplitudes during various displacement cycles. For LVDTs attached to the top face (TL series and TR series), data are presented for upward displacement peaks, while for LVDTs attached to the bottom face (BL series and BR series), data are presented for downward displacement peaks. Along the top face, the data show an “elongation bulge” associated with buckling of the top longitudinal reinforcement, which becomes apparent for the second set of cycles at 2.9% drift ratio, and is centered around 400 mm (15 in.) from the beam end. Along the bottom face, the data show a similar bulge associated with buckling of the bottom longitudinal reinforcement, which becomes apparent for the 2.9% drift cycles, and is centered around 381 mm (15 in.) from the beam end.

Figure 33 plots the histories of LVDTs spanning the buckling region for the top and bottom of the beam. As with Beam 1, the deformation measurements indicate that only tensile strains develop throughout the history. For loading in the direction that would tend to result in flexural compression, the gauges indicate partial crack closure (due to compression) except for the cycle in which significant buckling occurs, for which case the outward buckle results in a tensile reading of the displacement gauge.

Figure 34 plots histories of LVDTs and strain gauges. Figure 34(a) shows the similar strains measured with BL3 LVDT and a strain gauge LBI-OUT(2) at 363 mm (14.3 in.) and 352 mm (13.86 in.) from the fixed end of the beam, respectively. Figure 34(b) shows the significant difference in the strain measured at the top and bottom of a top longitudinal bar due to bending

after the second cycle, with a peak drift ratio of 1.8%. The histories of the vertical displacement transducers V1 to V5 (Figure 5) are shown in Figure 34(c). The strain in the vertical direction at 584mm from the fixed end of the beam began to exceed 0.2% for drift ratio larger than 1.8%. Similar levels of strain were observed 76 mm (3 in.) from the fixed end of the beam but only for negative drift ratios. The strains at 76 mm (3 in.) and 584 mm (23 in.) from the fixed end of the beam reached 0.6% at a drift ratio of 2.9%. The average concrete strain in the vertical direction, measured with LVDTs, at 1092 mm (43 in.) from the fixed end of the beam was similar to the strain in the stirrups measured with gauge TB2, as shown in Figure 34(d).

Fixed-end rotation, Θ_{fe} , due to strain penetration and bond slip of the longitudinal reinforcement in the anchorage block, made a notable contribution to the total drift of the beam. Figure 35 plots the drift ratio due to fixed-end rotation versus total drift ratio of the beam. The fixed end rotation was calculated based on the measurement of instruments TL1, TR1, BL1, and BR1 (Figure 5) as:

$$\Theta_{fe} = \frac{(\Delta_{TL1} + \Delta_{TR1})/2 - (\Delta_{BL1} + \Delta_{BR1})/2}{1270} \quad (1)$$

where Δ is the displacement measurement of the LVDTs in mm; 1270 mm (50 in.) is the distance between the top and the bottom LVDTs. For positive drift ratios: 29%, 38%, and 45% of the total drift ratio was due to fixed end rotation at peak drift ratio equal to 2.9% (first cycle), 2.9% (second cycle), 3.9%, respectively. The corresponding contributions for negative drift ratios were 36%, 57%, and 49%.




Figure 32 Beam 2: profiles of elongation measured between steel instrumentation rods normalized to gauge length. Note: negative elongation corresponds to shortening.




Figure 33 Beam 2: histories of elongation measured between steel instrumentation rods normalized to gauge length.




Figure 34 Beam 2: strain histories measured with strain gauges or displacement transducers at different locations of the beam.




Figure 35 Beam 2: drift due to fixed-end rotation versus total drift ratio.

1.10 COMPARISON OF MOMENT-DEFORMATION RELATIONS

Figure 36 plots the measured relations between resisting moments and drift ratios for the two beams. The moment-drift ratio response of the two beams is similar until the cycle to peak drift ratio of 1.8%. During the cycle with a peak drift ratio of 2.7%, longitudinal bar buckling resulted in rapid and significant loss of strength in Beam 1. In contrast, Beam 2 did not sustain strength loss until larger drift ratio (3.9%), and strength degradation was more gradual.




Figure 36 Relation between beam moment and beam drift ratio for Beams 1 and 2.

1.11 ESTIMATED SHEAR DEFORMATIONS

Instrumentation attached along the beam length near the anchor block enabled calculation of beam shear deformations. Figure 37 shows the relations between the beam shear and the estimated shear deformations within 1092 mm (43 in.) from the anchor block for the two beams. This relationship is plotted only for the cycles prior to the onset of longitudinal bar buckling; after this point, the LVDT measurements were distorted. For Beam 1, this includes cycles with drift ratio amplitude lower than and equal to 1.8%, while for Beam 2, the cycles with drift ratio amplitude less than and equal to 2.9% are included.

Although the peak applied force did not exceed 70% and 40% of the computed nominal shear strength provided by the hoops in Beams 1 and 2, respectively, shear degradation is noted through the progression of cycles for both specimens. Shear stiffness deterioration is also evident in the increased pinching of the moment-drift ratio curves at larger drift amplitudes (Figure 36). Overall, Beam 2 exhibited smaller shear deformations compared with Beam 1. During the last cycle with 1.8% drift ratio, approximate shear deformation of Beam 2 was roughly 50% of that measured in Beam 1 for the same amplitude cycle.




Figure 37 Relation between measured force and estimated shear deformations for Beams 1 and 2 and cycles preceding the bar buckling.

1.12 BUCKLING BEHAVIOR OF LONGITUDINAL REINFORCEMENT

In this laboratory study, inelastic cyclic buckling of the longitudinal reinforcement determined the progress of damage and strength deterioration. Previous experimental studies of cyclic inelastic behavior of reinforcing bars [Monti and Nuti 1992; Rodriguez et al. 1999] have demonstrated that the ratio of the unsupported length L_b to the bar diameter d_b is the primary factor that determines the buckling behavior of bars, while the steel material properties and loading history are secondary factors. In reinforced concrete specimens where the transverse reinforcement (spaced at s_h) provides the lateral support of the longitudinal bars, the ratio s_h / d_b can be considered as the primary factor affecting the buckling behavior.

In a reinforced concrete beam without prestressing, the longitudinal reinforcement strain history is characterized by increasing peak tensile strain as drift increases, with relatively little, if any, compressive strain. This behavior was observed for longitudinal bars in the present study (see Figure 17 and Figure 34). Rodriguez et al. [1999] hypothesized that buckling under this type of strain history would depend on the strain range ϵ_p , defined as the strain for which the bar is subjected to compressive stress after unloading from maximum tensile strain ϵ_s^+ , as illustrated in Figure 38. Rodriguez et al. [1999] shows that, if the strain range is represented in terms of ϵ_p , then data from tests with strain histories representative of both beams and columns can be combined. The results are shown in Figure 39. Also shown are the s_h / d_b ratios for Beams 1 and 2. Taking the average curve as representative, estimated strains at buckling are approximately 0.02 for Beam 1 and 0.06 for Beam 2.

For various reasons, the strain estimates from the preceding paragraph should be interpreted as very approximate representations of values expected in Beams 1 and 2. First, the basic material properties are inherently variable. Even in the tests reported by Rodriguez et al [1999], using a single source of reinforcement, a wide variation of buckling behavior was observed. Second, it is difficult in a test to identify the exact instant in which buckling initiates. Third, in a reinforced concrete beam, the concrete cover, if intact as it was in the case of these beams, acts to restrain buckling. Finally, stirrup yielding, which was apparent in the beam tests, results in reduced lateral support for the restrained bars. For these (and possibly other reasons), the buckling strain estimates should be considered only as rough approximations.

For Beam 1 the peak tensile strain of the longitudinal reinforcement measured during the cycle with 1.8% peak drift ratio (where buckling initiated) was about 2.0% (see Figure 17). This is in good agreement with the estimate using the curve of Figure 39. For Beam 2 the corresponding strain measured during the cycle with peak drift ratio equal to 2.9% (where buckling initiated) was about 2.5% (see Figure 34). This level of strain is significantly smaller than the strain estimate using the curve of Figure 39; however, during this cycle the stirrups experienced yielding (see Figure 34), resulting in increase of the effective s_h / d_b .




Figure 38 Cyclic stress strain of steel and definition of characteristics strains.




Figure 39 Strain range ϵ_p as function of L_b / d_b (taken as being equivalent to s_h / d_b) [after Rodriguez et al. (1999)].

1.13 COMPARISON OF MEASURED AND CALCULATED FLEXURAL RESPONSE

Conventional procedures for flexural response analysis were carried out for Beams 1 and 2. These include moment-curvature analyses, integration of flexural curvatures along the beam span to determine displacements, and analyses to estimate the onset of longitudinal reinforcement buckling. The procedures are summarized in the following paragraphs, followed by comparison between measured and calculated responses. See Appendix B for complete details.

Moment-curvature analyses were carried out using the usual assumption that strains vary linearly across the depth of the section. Longitudinal reinforcement was modeled based on the measured material properties including strain-hardening. Unconfined concrete (the cover) was modeled based on stress-strain relations obtained from cylinder tests. Effects of confinement on core concrete behavior were considered using a confined concrete model. Only monotonic loading was considered. Moment-curvature calculations were carried out using the software XTRACT [2009].

Displacement corresponding to onset of longitudinal reinforcement yielding, δ_y , was calculated using the approximation that the concrete was fully cracked along the entire beam length, with effective flexural rigidity EI taken equal to $0.3E_cI_g$, in which E_c = Young's modulus of concrete, and I_g is the second moment of inertia of the gross section. The multiplier 0.3 is in accordance with the multiplier for beam stiffness in ASCE 41 (2006). Displacement corresponding to ultimate curvature, δ_u , was calculated using a plastic-hinge model, and is taken as the sum of δ_y and the displacement due to rotation of a plastic hinge. Two plastic hinge rotations were considered. In one of the models, the rotation was taken equal to product of the calculated inelastic curvature capacity ($\phi_u - \phi_y$) and a plastic hinge length approximated as $l_p =$

$h/2$. In the other model, the rotation was taken equal to the Collapse Prevention rotation capacity for a conforming beam with low shear acting as a primary member, that is $\theta_p = 0.025$. If the member was redefined as a secondary member, then the same model could be extended to Collapse Prevention for secondary members, in which case the maximum displacement at residual capacity could be calculated using $\theta_p = 0.05$ in accordance with ASCE 41.

To estimate the curvature at buckling of longitudinal reinforcement, the relation between longitudinal bar strain and curvature was obtained from the moment-curvature analyses for both negative and positive curvature. Assuming that these relations were adequate representations of the relations for reversed cyclic loading, the positive and negative curvatures were gradually increased (analytically) until the longitudinal reinforcement strain difference (for the positive versus the negative curvatures) was equal to the strain range at buckling, ϵ_p , as identified in Figure 39. Corresponding displacement was then calculated using the plastic-hinge model, with ultimate curvature defined as the curvature corresponding to buckling.

Figure 40 and Figure 41 compare the measured responses of Beams 1 and 2 versus calculated responses. Calculated flexural stiffness to yield (based on $EI_{\text{eff}} = 0.3E_cI_g$) is higher than the measured stiffness. According to Elwood et al. [2007], actual stiffness of members with zero axial force tends on average to be lower than $0.3E_cI_g$, which is consistent with the results shown here. The measured flexural stiffness of Beam 1 at yield point was $0.13E_cI_g$, while that of Beam 2 was $0.16E_cI_g$.

The ASCE 41 moment-drift envelope follows the response of Beam 1 remarkably well, but underestimates drift capacity of Beam 2. Moment-drift response calculated using a bilinear approximation of the moment-curvature response (based on detailed moment-curvature analysis and a plastic-hinge length equal to $h/2$) grossly overestimates drift ratio capacity if longitudinal reinforcement buckling is ignored. Drift ratio capacity estimates are improved if longitudinal reinforcement buckling is taken into consideration.




Figure 40 Comparison of calculated response envelopes and the measured response of Beam 1.




Figure 41 Comparison of calculated response envelopes and the measured response of Beam 2.

1.14 RESIDUAL CRACK WIDTHS

Residual crack width provides a measure of serviceability and repair actions required following an earthquake. Appendix C contains crack width data for the tests. Although the data for Beam 1 were not consistently recorded, nonetheless they provide a useful record of the evolution of cracks throughout the test. The data for Beam 2 were more consistently recorded; they include crack widths for vertical (flexural) and inclined (shear) cracks recorded at displacement peaks and after the beam had completed a series of displacement cycles and was brought back to zero displacement. Figure 42 presents residual crack width (recorded at zero displacement) of the vertical cracks as function of prior peak drift ratio. Residual cracks widths increase at an increasing rate beyond the yield displacement, which corresponds to drift ratio around 0.5%.




Figure 42 Beam 2: residual crack width as function of peak drift ratio.

1.15 DESIGN RECOMMENDATION

Beam 1 was designed and detailed in accordance with ACI 318-08. Specifically, the hoop spacing within the intended plastic hinge zone was 270 mm (11 in.) based on the requirement of Section 21.5.3.2 that spacing not exceed the least of $d/4$, $8d_b$ of the smallest longitudinal bars, $24d_b$ of the hoop bars; and 12 in (305 mm). The beam was able to resist inelastic cyclic deformations up to an equivalent beam rotation of 0.027, at which point buckling of longitudinal reinforcement caused major loss of lateral force-resisting capacity. This performance is deemed, in general, to be unsatisfactory for a beam of a special moment frame, because rotations exceeding this rotation capacity generally can be anticipated for shaking at the MCE level. By decreasing the hoop spacing to 152 mm (6 in.), as was done for Beam 2, longitudinal reinforcement buckling resulting in strength decay was delayed until equivalent beam rotation of 0.039. This performance would generally be considered acceptable for a beam of a special moment frame.

Based on these observations, we recommend a Code Change Proposal to ACI 318-08, which replaces Section 21.5.3.2, Section 21.5.3.3, and associated commentary with the following:

CODE

21.5.3.2 — The first hoop shall be located not more than 50 mm (2 in.) from the face of a supporting member. Spacing of the hoops shall not exceed the smallest of (a), (b), and (c):

(a) $d/4$;

(b) Six times the diameter of the smallest primary flexural reinforcing bars excluding longitudinal skin reinforcement required by 10.6.7; and

(c) 6 in.

21.5.3.3 — Where hoops are required, primary flexural reinforcing bars closest to the tension and compression faces shall have lateral support conforming to 7.10.5.3 or 7.10.5.4. The spacing of laterally supported flexural reinforcing bars shall not exceed 14 in. Skin reinforcement required by 10.6.7 need not be laterally supported.

COMMENTARY

<<Replace Figure R21.5.3 and add new paragraph as follows:>>




Fig. R21.5.3—Examples of overlapping hoops and illustration of limit on maximum horizontal spacing of supported longitudinal bars.

For many years, the upper limit on hoop spacing was the smallest of $d/4$, 8 longitudinal bar diameters, 24 tie bar diameters, and 12 in. The upper limits were changed because of concerns about adequacy of longitudinal bar buckling restraint and confinement of large beams.

1.16 SUMMARY AND CONCLUSIONS

Two beams were designed, constructed, and tested under reversed cyclic displacements in a laboratory. The beams had depth of 1219 mm (48 in.) and width of 762 mm (30 in.). Both beams had five No. 36 (11) A706 Grade 60 longitudinal bars at top and bottom faces, resulting in longitudinal steel ratio equal to 0.58%. The beams satisfied ACI 318-08 code provisions for special moment frame beams. Transverse reinforcement comprised No. 16 (5) hoops made up of a stirrup closed by a crosstie, with an additional vertically oriented crosstie in each hoop set. In Beam 1 the hoop sets had longitudinal spacing of 279 mm (11 in.), while in Beam 2 the hoop sets had longitudinal spacing of 152 mm (6 in.). The ratios of hoop spacing to longitudinal bar diameter correspond to $s_h / d_b = 7.8$ and 4.25 in Beams 1 and 2, respectively. Both beams used normal-weight concrete with nominal compressive strength of 34 MPa (5000 psi). The beams were subjected to displacement reversals of increasing amplitude, simulating the effects of deformations due to strong earthquake shaking.

The following conclusions are drawn:

1. Beam 2 with reduced hoop spacing was capable of more displacement cycles and larger displacement amplitude than Beam 1 with wider hoop spacing. Beam 1 lost 38% of its peak resistance during a second cycle to peak drift ratio of 0.027. Beam 2 did not sustain strength loss until during the cycles to peak drift ratio of 0.039, and strength loss was more gradual. Beam 2 was capable of resisting one cycle at peak drift ratio of 0.053 while still resisting 80% of its peak strength.
2. Damage initiation and damage progress in both beams was dominated by buckling of the longitudinal reinforcement. For Beam 1, buckling initiated during a cycle with a peak drift ratio of 1.8%. Buckling became more extensive during the cycles with 2.7% peak drift ratio, when significant strength loss occurred. For Beam 2 with reduced hoop spacing, buckling was delayed until the first cycle with a peak drift ratio of 2.9% and became more extensive during the cycle with 3.9% peak drift ratio.
3. Tendency for reinforcing bar buckling depends on the ratio of hoop spacing to bar diameter (s_h / d_b) and on the strain history. Based on tests of bars in air, Rodriguez et al. [1999] hypothesized a relation between the strain range (defined as the strain for which the bar is subjected to compressive stress after unloading from maximum tensile strain) and s_h / d_b . According to that hypothesis, buckling in a beam is primarily a function of s_h / d_b and maximum tensile strain in the longitudinal reinforcement. For Beams 1 and 2, the Rodriguez et al. model suggests maximum longitudinal reinforcement strain capacity of 0.02 and 0.06, respectively. Measured tensile strains in the beams varied significantly, depending on the measurement device (LVDT or strain gauge) and measurement location. Overall, the strains were in the range suggested by the Rodriguez et al. model.
4. Longitudinal bar buckling in both beams initiated at the top of the beam where local concrete strength would be expected to be lowest. It seems more likely, however, that the tendency for earlier buckling at the top of the beam was influenced mainly by the

presence of the cap ties that closed the hoops at the top of the beam. Cap ties are likely to be most effective in closing a hoop where a slab is cast at the top of the beam. Where there is no slab, or where the beam is upturned with the slab at the bottom of the beam, the presence of cap ties creates a weakness at the top of the beam that should be considered when detailing the transverse reinforcement.

5. Beam 1 developed peak moment strength equal to $0.99M_{pr}$, where M_{pr} is probable moment strength calculated in accordance with ACI 318. Beam 2 developed peak moment strength equal to $1.10M_{pr}$.
6. Maximum nominal shear stresses for both beams were on the order of $0.14\sqrt{f'_c}$ MPa ($1.7\sqrt{f'_c}$ psi) using measured concrete compressive strength. For Beams 1 and 2, respectively, maximum shear forces were on the order of 70% and 40% of V_s , or 95% and 57% of ϕV_s , where $\phi = 0.75$ and V_s is calculated in accordance with ACI 318. Even though shear forces were less than provided shear strengths, some yielding of beam transverse reinforcement was recorded. Lateral support of longitudinal bars may have been reduced because of yielding of transverse reinforcement. This may have contributed to buckling of the longitudinal bars.
7. Rigid body displacements associated with slip of reinforcement from the anchorages constituted approximately 30% to 45% of the total beam displacement.
8. Initial stiffness was calculated using flexural rigidity equal to $0.3E_cI_g$, as recommended in ASCE 41. The coefficient 0.3 is intended to take into consideration the combined effects of concrete cracking and slip of reinforcement from the anchorages. Actual beam secant stiffness to yielding was less than this calculated value.
9. A plastic-hinge model based on ASCE 41 parameters was successful in representing the load-displacement behavior of Beam 1 but was overly conservative for Beam 2. Plastic-hinge models based on theoretical moment-curvature relations grossly overestimated displacement capacity of both beams if buckling was not taken into consideration. Results were improved if longitudinal reinforcement buckling according to the Rodriguez et al. [1999] model was taken into account. In all cases, the plastic-hinge length was taken equal to $h/2$ in accordance with ASCE 41.
10. Residual crack widths increased at an increasing rate beyond the yield displacement. At drift ratio of 0.02, residual crack width was 5 mm (0.2 in.).
11. In a large reinforced concrete beam similar to those tested in this study, with equal areas of top and bottom longitudinal reinforcement, flexural tension cracks formed during loading in one direction tend to remain open for loading in the reversed direction. Therefore, flexural compression is resisted mainly by the longitudinal reinforcement near the flexural compression face and not by the concrete. Thus, requirements for hoop reinforcement need not be based on considerations of concrete confinement, but instead these requirements should be based on considerations of beam shear and longitudinal reinforcement buckling restraint.

12. On the basis of the tests and supporting analyses, it is recommended that hoop spacing within the plastic-hinge region of special moment frame beams not exceed the least of $d/4$, $6d_b$ of the smallest longitudinal bars excluding skin reinforcement, and 150 mm (6 in.). A code change proposal for ACI 318-08, consistent with this recommendation, is presented in the main body of the report.

REFERENCES

- ACI (2008). *Building Code Requirements for Structural Concrete, ACI 318-08*, American Concrete Institute, Farmington Hills, MI.
- ACI (2011). *Building Code Requirements for Structural Concrete, ACI 318-11*, American Concrete Institute, Farmington Hills, MI.
- ASCE (2006). *Seismic Rehabilitation of Existing Buildings, ASCE/SEI Standard 41-06 including Supplement 1*, American Society of Civil Engineers, Reston, VA.
- Beckingsale C.W. (1980). Post-elastic behaviour of reinforced concrete beam-column joints, *Research Report No. 80-20*, Department of Civil Engineering, University of Canterbury, Christchurch, New Zealand, 398 pgs.
- Blakeley R.W.G., Megget L.M., Priestley M.J.N. (1975). Seismic performance of two full size reinforced concrete beam-column joint units, *Bull. New Zealand Soc. Earthq. Eng.*, 8(1): 38–69.
- Chang B.J., Hutchinson T.C., Englekirk R.E (2008) Experimental seismic performance evaluation of innovative beam-column subassemblies, *Report SSRP-08/01*, University of California, San Diego, CA.
- Elwood K.J., Matamoros A.B., Wallace J.W., Lehman D.E., Heintz J.A., Mitchell A.D., Moore M.A., Valley M.T., Lowes L.N., Comartin C.D., Moehle J.P. (2007). Update to ASCE/SEI 41 concrete provisions, *Earthq. Spectra*, 23(3): 493–523.
- Haselton C.B., Liel A.B., Deierlein G.G., Dean B.S., Chou, J.H. (2011). Seismic collapse safety of reinforced concrete buildings: I. assessment of ductile moment frames, ASCE, *J. Struct. Eng.*, 137: 481–491.
- Monti G., Nuti C. (1992). Nonlinear cyclic behavior of reinforcing bars including buckling, ASCE, *J. Struct. Eng.*, 118(12): 3268–3284.
- Popov E.P., Bertero V.V., Krawinkler H. (1972). Cyclic behavior of three reinforced concrete flexural members with high shear, *Report No. EERC 72-5*, Earthquake Engineering Research Center, University of California, Berkeley, CA.
- Restrepo J.I., Park R., Buchanan A. (1990) Seismic behaviour of connections between precast concrete elements, *Research Report 93-3*, Department of Civil Engineering, University of Canterbury, Christchurch, New Zealand.
- Rodriguez M., Botero J., Villa J. (1999). Cyclic stress-strain behavior of reinforcing steel including effect of buckling, *J. Struct. Eng.*, 125 (6): 605–612.
- Visnjic T., Panagiotou M., Moehle J.P. (2012). Seismic response of 20-story reinforced concrete special moment resisting frames designed with current code provisions, *Report No. UCB/SEMM-2012/02*, Department of Civil and Environmental Engineering, University of California, Berkeley, CA.
- Warcholik G., Priestley, M.J.N. (1997). Structural systems research project: High strength concrete joints tests, *Report No. TR-97/10*, University of California, San Diego, CA.
- XTRACT (2009). XTRACT, version 3.0.8. TRC/Imbsen Software Systems, <http://www.imbsen.com/xtract.htm>.

APPENDIX A: RECORDED INSTRUMENTATION DATA HISTORIES




Figure A.1 Beam 1: histories of displacement transducers.




Figure A.2 Beam 1: histories of displacement transducers.




Figure A.3 Beam 1: histories of displacement transducers.




Figure A.4 Beam 1: histories of strain gauges.




Figure A.5 Beam 1: histories of strain gauges.




Figure A.6 Beam 1: histories of strain gauges.




Figure A.7 Beam 1: histories of strain gauges.




Figure A.8 Beam 1: histories of displacement transducers.




Figure A.9 Beam 2: histories of displacement transducers.




Figure A.10 Beam 2: histories of displacement transducers.




Figure A.11 Beam 2: histories of strain gauges.




Figure A.12 Beam 2: histories of strain gauges.




Figure A.13 Beam 2: histories of strain gauges.




Figure A.14 Beams 2: histories of strain gauges.





Figure A.15 Beam 2: histories of strain gauges..

APPENDIX B: FLEXURAL RESPONSE CALCULATIONS

Beam 1



Core Dimensions:

Core beam width: $b_c = 30 - 3 = 27$ in.

Core beam depth: $h_c = 48 - 3 = 45$ in.

Transverse Reinforcement: 3-legged #5 bars

Transverse reinforcement area: $A_v = 3 * 0.31 = 0.93$ in.²

Volumetric transverse reinforcement ratio: $\rho_s = 0.93 / (27 * 11) = 0.313\%$

Calculation of Concrete Confinement:

The confinement stress equals: $f_1 = f_s * A_v / (b_c * s) = 66 * 0.93 / (27 * 11) = 0.2067$, where $f_s = f_y = 66$ ksi is the transverse reinforcement yield strength, A_v is the transverse reinforcement ratio, b_c is the core beam width, and s is the transverse reinforcement spacing.




Figure a: Confinement effectiveness for various confinement configurations and hoop spacing

Using the s/b_c ratio, the effectiveness coefficient is calculated for a rectangular beam with a cross-tie. For $s/b_c = 11/27 = 0.4074$ – $k_e = 0.43$. The effective confinement stress equals: $f_{le} = k_e * f_l = 0.43 * 0.2067 = 0.0889$ ksi.




Figure b: Confined concrete strength as function of effective confinement stresses

For $f_{le} / f'_c = 0.0889 / 5.82 = 0.0153$ - $f'_{cc} / f'_c = 1.09$, where f'_{cc} is the confined concrete compressive strength, and f'_c is the unconfined concrete strength.

The ultimate confined concrete compressive strain capacity: $\epsilon_{cu} = 0.004 + 0.17 * f_{le} / f'_c = 0.004 + 0.25 * 0.00889 / 5.82 = 0.00782$.

The confined concrete compressive strain at peak stress is: $\epsilon_{cc} = \epsilon_0 * [1 + 5*(f'_{cc} / f'_c - 1)] = 0.003 * [1 + 5*(1.09 - 1.00)] = 0.00435$, where ϵ_0 corresponds to the unconfined concrete strain at peak stress.

Moment Curvature Calculation:

Moment curvature calculation was performed using XTract analysis software. The geometry of the analyzed cross section is shown below:




Figure c: Geometric properties of beam cross section

It should be noted that for the analysis of the beam cross section the 8 No. 4 longitudinal bars that act as skin reinforcement were not included in the moment curvature analysis due to the lack of full development in the anchorage block.

Cited below are the material properties utilized for the moment curvature calculation of Beam 1.

Steel 1¹

Input Parameters:

Yield Stress:	73.00 ksi
Fracture Stress:	105.0 ksi
Yield Strain:	2.517E-3
Strain at Strain Hardening:	12.00E-3
Failure Strain:	.1500
Elastic Modulus:	29.00E+3 ksi
Additional Information:	Symmetric Tension and Comp.

Model Details:

$$\begin{aligned} \text{For Strain - } \varepsilon < \varepsilon_y & \quad f_s = E \cdot \varepsilon \\ \text{For Strain - } \varepsilon < \varepsilon_{sh} & \quad f_s = f_y \\ \text{For Strain - } \varepsilon < \varepsilon_{su} & \quad f_s = f_u - (f_u - f_y) \left(\frac{\varepsilon_{su} - \varepsilon}{\varepsilon_{su} - \varepsilon_{sh}} \right)^2 \end{aligned}$$

ε = Steel Strain

f_s = Steel Stress

f_y = Yield Stress

f_u = Fracture Stress

ε_y = Yield Strain

ε_{sh} = Strain at Strain Hardening

ε_{su} = Failure Strain

E = Elastic Modulus




Figure d: Steel uniaxial material behavior

¹ The moment curvature analysis does not take into account the effect of buckling of longitudinal steel reinforcement that was observed during the experiment.


Confined Concrete²

Input Parameters:

Ultimate Compressive Strain: 7.820E-3
 Compression Yield Strain: 1.400E-3
 Tensile Yield Strain: 1.300E-3

Material Color States:

☐ Color State



Stress Strain Points:

Strain	Stress (ksi)	Strain	Stress (ksi)
-.2600E-3	0	3.500E-3	6.266
-.1300E-3	-.5653	3.750E-3	6.308
-.1200E-3	-.5218	4.000E-3	6.332
-.1100E-3	-.4783	4.250E-3	6.343
-.1000E-3	-.4348	4.500E-3	6.342
0	0	4.750E-3	6.332
.2500E-3	1.059	5.000E-3	6.314
.5000E-3	2.020	5.250E-3	6.289
.7500E-3	2.859	5.500E-3	6.260
1.000E-3	3.573	5.750E-3	6.227
1.250E-3	4.170	6.000E-3	6.190
1.500E-3	4.661	7.820E-3	5.873
1.750E-3	5.061		
2.000E-3	5.383		
2.250E-3	5.639		
2.500E-3	5.841		
2.750E-3	5.997		
3.000E-3	6.116		
3.250E-3	6.204		

Figure e: Confined concrete material behavior

² The confined concrete material behavior was modeled according to the relationship suggested by Mander et al. (1988).

Unconfined Concrete³

Input Parameters:

Compression Yield Strain: 1.400E-3

Tensile Yield Strain: 1.300E-3

Material Color States:

☐ Color State

Stress Strain Points:

Strain	Stress (ksi)
-2.600E-3	0
-1.300E-3	-5.653
-1.200E-3	-5.218
-1.100E-3	-4.783
-1.000E-3	-4.348
0	0
.5000E-3	2.073
1.000E-3	3.714
1.500E-3	4.813
2.000E-3	5.446
2.500E-3	5.742
3.000E-3	5.820
3.500E-3	5.765
4.000E-3	5.635
5.000E-3	5.274
6.000E-3	4.886
8.000E-3	0




Figure f: Unconfined concrete material behavior

³ The unconfined concrete material behavior was modeled according to the relationship suggested by Mander et al. (1988).

The analytical results of moment curvature analysis are presented below:




Figure g: Moment curvature analysis

As illustrated in the figure above:

The estimated ultimate moment strength: $M_{ult} = 34,880$ kip-in.

The estimated ultimate moment curvature: $\phi_{ult} = 3.60 * 10^{-3}$ in.⁻¹

An equivalent bilinear moment curvature curve was also used to approximate the cross-section behavior. The following values were used for the bi-linearization of the moment curvature curve:

Effective curvature stiffness = $0.3 * E_{concrete} * I_g = 0.30 * 4348.47 * 276480 = 360.679 * 10^6$ kip-in.², where $E_{concrete}$ is the concrete Young's Modulus, calculated as 57,000 sqrt (f'_c) according to ACI 318-08, I_g is the second moment of inertia of the beam gross cross section, and 0.30 is the modification cracking factor according to ASCE 41 (Supplement 1).

Approximate yielding moment strength: $M_{yield} = 23650$ kip-in.

Approximate yielding moment curvature: $\phi_{yield} = 6.557 * 10^{-5}$

Approximate ultimate moment strength: $M_{ult} = 34,880$ kip-in.

Approximate ultimate moment curvature: $\phi_{ult} = 3.60 * 10^{-3}$ in.⁻¹

Calculation of Beam Tip Displacement

To evaluate the analytical results with the beam tip displacement was calculated analytically and compared to the observed experimental results. For the analytical calculation of beam tip displacement, two approaches were employed:

- use the bilinear approximation of moment curvature analysis assuming that the material nonlinear behavior was concentrated in a plastic hinge zone $l_p = 0.5 * h$, where h is the beam depth
- use the moment rotation values as suggested by ASCE-41 for modeling of beam members

Bilinear Approximation

	Moment (kip-in)	Displacement (in.)	Drift Ratio ⁴
Undeformed State	0.0	0.00000	0.0000
Reinforcement Yielding ⁵	23,650.0	0.49178	0.0033
Ultimate Strength ⁵	34,880.0	11.6163	0.0774




Figure h: Moment – drift ratio curve

⁴ The drift ratio was calculated as (displacement) / (beam length) (=150 in.).

⁵ The calculation of the tip displacement for the states where yielding and ultimate moment strength occurs was performed using integration of the calculated curvature as follows: $\Delta_y = \phi'_y * l^2 / 3$ and $\Delta_{ult} = \phi_y * l^2 / 3 + (\phi_{ult} - \phi_y) * l_p * (l - l_p / 2)$, where ϕ'_y corresponds to the curvature where reinforcement yielding is observed, $\phi_y = \phi'_y * M_{ult} / M_y = 6.557 * 10^{-5} * 34,880 / 23,650 = 9.67 * 10^{-5} \text{ in.}^{-1}$.

ASCE -41 Approximation

The probable moment M_{pr} according to ASCE-41 is calculated using nominal material properties ($f'_c = 5$ ksi and $1.25 * f_y = 1.25 * 60 = 75.0$ ksi), $M_{pr} = 25,340$ kip-in.

For the beam section, the following properties apply:

$$(\rho - \rho') / \rho_{bal} = 0.0$$

transverse reinforcement has code conforming details with 135° hooks

$$V / [b_w * d * \text{sqrt}(f'_c)] = 168,933.33 / (27 * 45.17 * 76.30) = 1.815 < 3.00, \text{ assuming } V = V_{pr} = 25,340 / 150 = 168.93 \text{ kips}$$

Stirrup spacing 11 in $< d/2$

According to ASCE 41 (Supplement 1), the beam is suggested to be simulated using lumped plasticity model with the following backbone curve:




Figure i: Backbone curve (ASCE-41)

The beam is controlled by flexure, therefore the deformation quantities according to Table 6-7 of ASCE-41 are as follows: $a = 0.025$, $b = 0.05$, and $c = 0.20$

Substituting the above values and using the results of moment curvature analysis, we have:

	Moment (kip-in.)	Displacement (in.)	Drift Ratio ⁶
Undeformed State	0.0	0.00000	0.0000
Reinforcement Yielding ⁷	23,650.0	0.49178	0.0033
Ultimate Strength ⁷	25,340.0	4.27692	0.0285
Residual Strength ⁷	4730.0	7.59836	0.0507

⁶ The drift ratio was calculated as (displacement) / (beam length) (=150 in.).

⁷ The calculation of the tip displacement for the states where yielding, ultimate, and residual moment strength occurs was performed using integration of the calculated curvature as follows: Δ_y (calculated using effective stiffness), $\Delta_{ult} = (M_y / EI_{eff}) * l^2 / 3 + 0.025 * l$ and $\Delta_{res} = (M_{res} / EI_{eff}) * l^2 / 3 + 0.050 * l$.




Figure j: Moment – drift ratio curve (according to ASCE-41)

Comparison of Analytical Approximations with Experimental Results




Figure k: Comparison of analytical and experimental results





Figure 1: Comparison of analytical and experimental results (includes estimated point where buckling occurs according to Rodriguez)

Beam 2



Core Dimensions:

Core beam width: $b_c = 30 - 3 = 27$ in.

Core beam depth: $h_c = 48 - 3 = 45$ in.

Transverse Reinforcement: 3-legged #5 bars

Transverse Reinforcement Area: $A_v = 3 * 0.31 = 0.93$ in.²

Volumetric Transverse Reinforcement Ratio: $\rho_s = 0.93 / (27 * 6) = 0.574\%$

Calculation of Concrete Confinement:

The confinement stress equals: $f_l = f_s * A_v / (b_c * s) = 66 * 0.93 / (27 * 6) = 0.3789$, where $f_s = f_y = 66$ ksi is the transverse reinforcement yield strength, A_v is the transverse reinforcement ratio, and b_c is the core beam width and s is the transverse reinforcement spacing.




Figure a: Confinement effectiveness for various confinement configurations and hoop spacing

Using the s/b_c ratio the effectiveness coefficient is calculated for a rectangular beam with a cross-tie. For $s/b_c = 6/27 = 0.222 - k_e = 0.57$.

The effective confinement stress equals: $f_{1e} = k_e * f_l = 0.57 * 0.3789 = 0.2160$ ksi.




Figure b: Confined concrete strength as function of effective confinement stresses

For $f_{1e} / f'_c = 0.2160 / 6.13 = 0.0352$ - $f'_{cc} / f'_c = 1.22$, where f'_{cc} is the confined concrete compressive strength, f'_c is the unconfined concrete strength.

The ultimate confined concrete compressive strain capacity: $\epsilon_{cu} = 0.004 + 0.17 * f_{1e} / f'_c = 0.004 + 0.25 * 0.2160 / 6.13 = 0.0128$.

The confined concrete compressive strain at peak stress is: $\epsilon_{cc} = \epsilon_0 * [1 + 5 * (f'_{cc} / f'_c - 1)] = 0.003 * [1 + 5 * (1.09 - 1.00)] = 0.0063$, where ϵ_0 corresponds to the unconfined concrete strain at peak stress.

Moment Curvature Calculation:

Moment curvature calculation was performed using XTract analysis software. The geometry of the analyzed cross section is shown below:




Figure c: Geometric properties of beam cross section

It should be noted that for the analysis of the beam cross section the 8 No. 4 longitudinal bars that act as skin reinforcement were not included in the moment curvature analysis due to the lack of full development in the anchorage block.

Cited below the material properties utilized for the moment curvature calculation of beam 1.

Steel 1⁸

Input Parameters:

Yield Stress:	73.00 ksi
Fracture Stress:	105.0 ksi
Yield Strain:	2.517E-3
Strain at Strain Hardening:	12.00E-3
Failure Strain:	.1500
Elastic Modulus:	29.00E+3 ksi
Additional Information:	Symmetric Tension and Comp.

Model Details:

$$\begin{aligned} \text{For Strain - } \varepsilon < \varepsilon_y & \quad f_s = E \cdot \varepsilon \\ \text{For Strain - } \varepsilon < \varepsilon_{sh} & \quad f_s = f_y \\ \text{For Strain - } \varepsilon < \varepsilon_{su} & \quad f_s = f_u - (f_u - f_y) \left(\frac{\varepsilon_{su} - \varepsilon}{\varepsilon_{su} - \varepsilon_{sh}} \right)^2 \end{aligned}$$

ε = Steel Strain

f_s = Steel Stress

f_y = Yield Stress

f_u = Fracture Stress

ε_y = Yield Strain

ε_{sh} = Strain at Strain Hardening

ε_{su} = Failure Strain

E = Elastic Modulus




Figure d: Steel uniaxial material behavior

⁸ The moment curvature analysis is not taking into account the effect of buckling of longitudinal steel reinforcement which was observed in the during the experiment


Confined Concrete⁹

Input Parameters:

Ultimate Compressive Strain: 12.80E-3
 Compression Yield Strain: 1.400E-3
 Tensile Yield Strain: 1.300E-3

Material Color States:

☐ Color State



Stress Strain Points:

Strain	Stress (ksi)	Strain	Stress (ksi)
-2.600E-3	0	3.500E-3	6.976
-1.300E-3	-5.802	3.750E-3	7.088
-1.200E-3	-5.355	4.000E-3	7.180
-1.100E-3	-4.909	4.250E-3	7.256
-1.000E-3	-4.463	4.500E-3	7.317
0	0	4.750E-3	7.365
.2500E-3	1.079	5.000E-3	7.403
.5000E-3	2.052	5.250E-3	7.432
.7500E-3	2.906	5.500E-3	7.453
1.000E-3	3.644	5.750E-3	7.467
1.250E-3	4.276	6.000E-3	7.475
1.500E-3	4.814	7.820E-3	7.419
1.750E-3	5.270	12.80E-3	6.925
2.000E-3	5.656		
2.250E-3	5.982		
2.500E-3	6.256		
2.750E-3	6.487		
3.000E-3	6.680		
3.250E-3	6.842		

Figure e: Confined concrete material behavior

⁹ The confined concrete material behavior was modeled according to the relationship as suggested by Mander et al. (1988).

Unconfined Concrete¹⁰

Input Parameters:

Compression Yield Strain: 1.400E-3

Tensile Yield Strain: 1.300E-3

Material Color States:

☐ Color State

Stress Strain Points:

Strain	Stress (ksi)
-.2600E-3	0
-.1300E-3	-.5802
-.1200E-3	-.5355
-.1100E-3	-.4909
-.1000E-3	-.4463
0	0
.5000E-3	2.138
1.000E-3	3.860
1.500E-3	5.034
2.000E-3	5.720
2.500E-3	6.044
3.000E-3	6.130
3.500E-3	6.069
4.000E-3	5.925
5.000E-3	5.526
6.000E-3	5.098
8.000E-3	0




Figure f: Unconfined concrete material behavior

The analytical results of moment curvature analysis are presented below.

¹⁰ The unconfined concrete material behavior was modeled according to the relationship as suggested by Mander et al. (1988).




Figure g: Moment curvature analysis

As illustrated in the figure above:

The estimated ultimate moment strength: $M_{ult} = 34,920$ kip-in.

The estimated ultimate moment curvature: $\phi_{ult} = 3.60 * 10^{-3}$ in.⁻¹

An equivalent bilinear moment curvature curve was also used to approximate the cross section behavior. The following values were used for the bi-linearization of the moment curvature curve:

Effective Curvature Stiffness = $0.3 * E_{concrete} * I_g = 0.30 * 4462.78 * 276,480 = 370.1608 * 10^6$ kip-in.², where $E_{concrete}$ is the concrete Young's modulus, calculated as 57,000 sqrt (f'_c) according to ACI 318-08, I_g is the second moment of inertia of the beam gross cross section and 0.30 is the modification cracking factor according to ASCE 41 (Supplement 1).

Approximate yielding moment strength: $M_{yield} = 23,680$ kip -in.

Approximate yielding moment curvature: $\phi_{yield} = 6.397 * 10^{-5}$

Approximate ultimate moment strength: $M_{ult} = 34920$ kip-in.

Approximate ultimate moment curvature: $\phi_{ult} = 360 * 10^{-5}$ in.⁻¹

Calculation of Beam Tip Displacement

To evaluate the analytical results with the beam tip displacement was calculated analytically and compared to the observed experimental results.

For the analytical calculation of beam tip displacement two approaches were employed:

- Use the bilinear approximation of moment curvature analysis assuming that the material non-linear behavior was concentrated in a plastic hinge zone $l_p = 0.5 * h$, where h is the beam depth
- Use the moment rotation values as suggested by ASCE-41 for modeling of beam members

Bilinear Approximation

	Moment (kip-in.)	Displacement (in.)	Drift Ratio ¹¹
Undeformed State	0.0	0.00000	0.0000
Reinforcement Yielding ¹²	23,680.0	0.47979	0.0032
Ultimate Strength ¹²	34,920.0	11.6109	0.0774




Figure h: Moment – drift ratio curve

¹¹ The drift ratio was calculated as (displacement) / (beam length) (=150 in.).

¹² The calculation of the tip displacement for the states where yielding and ultimate moment strength occurs was performed using integration of the calculated curvature as follows: $\Delta_y = \phi'_y * l^2 / 3$ and $\Delta_{ult} = \phi_y * l^2 / 3 + (\phi_{ult} - \phi_y) * l_p * (l - l_p / 2)$, where ϕ'_y corresponds to the curvature where reinforcement yielding is observed, $\phi_y = \phi'_y * M_{ult} / M_y = 6.397 * 10^{-5} * 34,920 / 23,680 = 9.43 * 10^{-5} \text{ in.}^{-1}$.

ASCE-41 Approximation

The probable moment M_{pr} according to ASCE-41 is calculated using nominal material properties ($f'_c = 5$ ksi and $1.25 * f_y = 1.25 * 60 = 75.0$ ksi), $M_{pr} = 25,340$ kip-in. For the beam section the following properties apply:

$$(\rho - \rho') / \rho_{bal} = 0.0$$

transverse reinforcement has code conforming details with 135° hooks

$$V / [bw * d * \text{sqrt}(f'_c)] = 168,933.33 / (27 * 45.17 * 78.29) = 1.77 < 3.00, \text{ assuming } V = V_{pr} = 25340 / 150 = 168.93 \text{ kips}$$

Stirrup spacing 6 in $< d/2$

According to ASCE 41 (Supplement 1) the beam is suggested to be simulated using lumped plasticity model with the following backbone curve:




Figure i: Backbone curve (ASCE-41)

The beam is controlled by flexure so the deformation quantities according to Table 6-7 of ASCE-41 are the following: $a = 0.025$, $b = 0.05$, and $c = 0.20$.

Substituting the above values and using the results of moment curvature analysis we have:

	Moment (kip-in.)	Displacement (in.)	Drift Ratio ¹³
Undeformed State	0.0	0.00000	0.0000
Reinforcement Yielding ¹⁴	23,680.0	0.47979	0.0032
Ultimate Strength ¹⁴	25,340.0	4.26343	0.0284
Residual Strength ¹⁴	4736.0	7.59596	0.0506

¹³ The drift ratio was calculated as (displacement) / (beam length) (=150 in.).

¹⁴ The calculation of the tip displacement for the states where yielding and ultimate moment strength occurs was performed using integration of the calculated curvature as follows: Δ_y (calculated using effective stiffness), $\Delta_{ult} = (M_y / EI_{eff}) * l^2 / 3 + 0.025 * l$ and $\Delta_{res} = (M_{res} / EI_{eff}) * l^2 / 3 + 0.050 * l$.




Figure j: Moment–drift ratio curve (according to ASCE-41)

Comparison of Analytical Approximations with Experimental Results




Figure k: Comparison of analytical and experimental results




Figure 1: Comparison of analytical and experimental results (includes estimated point where buckling occurs according to Rodriguez)

APPENDIX C: RECORDED CRACK WIDTHS

Beam 1

step	# of cycles	tip displ. (mm)	drift ratio	μ_{Δ}	current cycle #	direction of beam tip displacement	max. diagonal crack width (mm)	max. vertical crack width (mm)	max. interface crack width (mm)
1	3	3	0.07	0.1	1	down			
					1	up			
					1	zero			
2	3	7	0.18	0.3	1	down		0.25	
					2	up		0.2	
					2	zero			
3	3	11	0.28	0.5	1	down		0.33	
					1	up			
					1	zero			
4	3	14	0.38	0.8	1	down		0.6	
					1	up			
					1	zero			
5	3	31	0.81	1.1	1	down		1	0.6
					1	up			
					1	zero			
6	3	46	1.2	2.1	1	down	1.5		3
					1	up			
					1	zero			
7	1	13	0.33	0.7	1	n/a			2
8	2	69	1.8	3.2	1	down	3	2.5	4
					1	up			
					1	zero			
9	1	13	0.33	0.7	1	n/a			
10	2	103	2.7	4.2	1	down	5		5
					1	up	5		
					3	zero		2.5	
11	1	13	0.33	0.7	1	n/a			
12	2	139	3.6	6.4	1	down	25		
					1	up			
					1	zero			
13	1	13	0.33	0.7	1	n/a			
14	1	194	5.1	8.5	1	n/a			
15	1	13	0.33	0.7	1	n/a			
16	1	210	5.5	11.7	1	n/a			

Beam 2

step	# of cycles	tip displ. (mm)	drift ratio	μ_{Δ}	current cycle #	direction of beam tip displacement	max. diagonal crack width (mm)	max. vertical crack width (mm)	max. interface crack width (mm)
1	3	3	0.07	0.2	1	down		0.08	
						up			
					3	zero			
2	3	6	0.16	0.3	1	down		0.3	
						up			
					3	zero		0.33	
3	3	11	0.28	0.6	1	down	0.2	0.4	
						up	0.2	0.4	
					3	zero	0.1	0.25	
4	3	15	0.4	0.9	1	down	0.3	0.4	
						up	0.2	0.3	
					3	zero	0.15	0.25	
5	3	33	0.87	1.9	1	down	0.5	0.5	
						up	0.3	0.5	
					3	zero	0.15	0.2	
6	3	46	1.2	2.6	1	down	0.6	1	
						up	0.6	1.25	
					3	zero	0.3	0.5	
7	1	13	0.33	0.7	1	n/a	n/a		
8	2	69	1.8	3.9	1	down	1.5	2	
					1	up	0.6	2	
					3	zero	1.5	2	
9	1	13	0.33	0.7	1	n/a	n/a		
10	2	109	2.9	6.2	1	down	3	4	
					1	up	1.5	3	
					3	zero	4	5	
11	1	13	0.33	0.7	1	n/a	n/a		
12	2	147	3.9	8.3	1	down	5	6	11
					1	up	6	8	20
					2	zero	7	15	20
13	1	13	0.33	0.7	1	cycle omitted			
14	1	203	5.3	11.4	1	down	7	9	
15	1	13	0.33	0.7	1	n/a			
16	1	222 (-244)	5.8 (-6.4)	12.5 (-13.7)	1	n/a			

PEER REPORTS

PEER reports are available as a free PDF download from http://peer.berkeley.edu/publications/peer_reports_complete.html. Printed hard copies of PEER reports can be ordered directly from our printer by following the instructions at http://peer.berkeley.edu/publications/peer_reports.html. For other related questions about the PEER Report Series, contact the Pacific Earthquake Engineering Research Center, 325 Davis Hall mail code 1792, Berkeley, CA 94720. Tel.: (510) 642-3437; Fax: (510) 665-1655; Email: peer_editor@berkeley.edu

- PEER 2013/16** *Effect of hoop reinforcement spacing on the cyclic response of large reinforced concrete special moment frame beams.* Marios Panagiotou, Tea Visnjic, Grigorios Antonellis, Panagiotis Galanis, and Jack P. Moehle. June 2013.
- PEER 2013/15** *publication pending*
- PEER 2013/14** *publication pending*
- PEER 2013/13** *publication pending*
- PEER 2013/12** *Nonlinear Horizontal Site Response for the NGA-West2 Project.* Ronnie Kamai, Norman A. Abramson, Walter J. Silva. May 2013.
- PEER 2013/11** *Epistemic Uncertainty for NGA-West2 Models.* Linda Al Atik and Robert R. Youngs. May 2013.
- PEER 2013/10** *NGA-West 2 Models for Ground-Motion Directionality.* Shrey K. Shahi and Jack W. Baker. May 2013.
- PEER 2013/09** *Final Report of the NGA-West2 Directivity Working Group.* Paul Spudich, Jeffrey R. Bayless, Jack W. Baker, Brian S.J. Chiou, Badie Rowshandel, Shrey Shahi, and Paul Somerville. May 2013.
- PEER 2013/08** *NGA-West2 Model for Estimating Average Horizontal Values of Pseudo-Absolute Spectral Accelerations Generated by Crustal Earthquakes.* I. M. Idriss. May 2013.
- PEER 2013/07** *Update of the Chiou and Youngs NGA Ground Motion Model for Average Horizontal Component of Peak Ground Motion and Response Spectra.* Brian Chiou and Robert Youngs. May 2013.
- PEER 2013/06** *NGA-West2 Campbell-Bozorgnia Ground Motion Model for the Horizontal Components of PGA, PGV, and 5%-Damped Elastic Pseudo-Acceleration Response Spectra for Periods Ranging from 0.01 to 10 sec.* Kenneth W. Campbell and Yousef Bozorgnia. May 2013.
- PEER 2013/05** *NGA-West 2 Equations for Predicting Response Spectral Accelerations for Shallow Crustal Earthquakes.* David M. Boore, Jonathan P. Stewart, Emel Seyhan, Gail M. Atkinson. May 2013.
- PEER 2013/04** *Update of the AS08 Ground-Motion Prediction Equations Based on the NGA-West2 Data Set.* Norman Abrahamson, Walter Silva, and Ronnie Kamai. May 2013.
- PEER 2013/03** *PEER NGA-West2 Database.* Timothy D. Ancheta, Robert B. Darragh, Jonathan P. Stewart, Emel Seyhan, Walter J. Silva, Brian S.J. Chiou, Katie E. Wooddell, Robert W. Graves, Albert R. Kottke, David M. Boore, Tadahihiro Kishida, and Jennifer L. Donahue. May 2013.
- PEER 2013/02** *Hybrid Simulation of the Seismic Response of Squat Reinforced Concrete Shear Walls.* Catherine A. Whyte and Bozidar Stojadinovic. May 2013.
- PEER 2013/01** *Housing Recovery in Chile: A Qualitative Mid-program Review.* Mary C. Comerio. February 2013.
- PEER 2012/08** *Guidelines for Estimation of Shear Wave Velocity.* Bernard R. Wair, Jason T. DeJong, and Thomas Shantz. December 2012.
- PEER 2012/07** *Earthquake Engineering for Resilient Communities: 2012 PEER Internship Program Research Report Collection.* Heidi Tremayne (Editor), Stephen A. Mahin (Editor), Collin Anderson, Dustin Cook, Michael Erceg, Carlos Esparza, Jose Jimenez, Dorian Krausz, Andrew Lo, Stephanie Lopez, Nicole McCurdy, Paul Shipman, Alexander Strum, Eduardo Vega. December 2012.
- PEER 2012/06** *Fragilities for Precarious Rocks at Yucca Mountain.* Matthew D. Purvance, Rasool Anooshehpour, and James N. Brune. December 2012.
- PEER 2012/05** *Development of Simplified Analysis Procedure for Piles in Laterally Spreading Layered Soils.* Christopher R. McGann, Pedro Arduino, and Peter Mackenzie-Helnwein. December 2012.
- PEER 2012/04** *Unbonded Pre-Tensioned Columns for Bridges in Seismic Regions.* Phillip M. Davis, Todd M. Janes, Marc O. Eberhard, and John F. Stanton. December 2012.

- PEER 2012/03** *Experimental and Analytical Studies on Reinforced Concrete Buildings with Seismically Vulnerable Beam-Column Joints.* Sangjoon Park and Khalid M. Mosalam. October 2012.
- PEER 2012/02** *Seismic Performance of Reinforced Concrete Bridges Allowed to Uplift during Multi-Directional Excitation.* Andres Oscar Espinoza and Stephen A. Mahin. July 2012.
- PEER 2012/01** *Spectral Damping Scaling Factors for Shallow Crustal Earthquakes in Active Tectonic Regions.* Sanaz Rezaeian, Yousef Bozorgnia, I. M. Idriss, Kenneth Campbell, Norman Abrahamson, and Walter Silva. July 2012.
- PEER 2011/10** *Earthquake Engineering for Resilient Communities: 2011 PEER Internship Program Research Report Collection.* Eds. Heidi Faison and Stephen A. Mahin. December 2011.
- PEER 2011/09** *Calibration of Semi-Stochastic Procedure for Simulating High-Frequency Ground Motions.* Jonathan P. Stewart, Emel Seyhan, and Robert W. Graves. December 2011.
- PEER 2011/08** *Water Supply in regard to Fire Following Earthquake.* Charles Scawthorn. November 2011.
- PEER 2011/07** *Seismic Risk Management in Urban Areas. Proceedings of a U.S.-Iran-Turkey Seismic Workshop.* September 2011.
- PEER 2011/06** *The Use of Base Isolation Systems to Achieve Complex Seismic Performance Objectives.* Troy A. Morgan and Stephen A. Mahin. July 2011.
- PEER 2011/05** *Case Studies of the Seismic Performance of Tall Buildings Designed by Alternative Means.* Task 12 Report for the Tall Buildings Initiative. Jack Moehle, Yousef Bozorgnia, Nirmal Jayaram, Pierson Jones, Mohsen Rahnama, Nilesh Shome, Zeynep Tuna, John Wallace, Tony Yang, and Farzin Zareian. July 2011.
- PEER 2011/04** *Recommended Design Practice for Pile Foundations in Laterally Spreading Ground.* Scott A. Ashford, Ross W. Boulanger, and Scott J. Brandenberg. June 2011.
- PEER 2011/03** *New Ground Motion Selection Procedures and Selected Motions for the PEER Transportation Research Program.* Jack W. Baker, Ting Lin, Shrey K. Shahi, and Nirmal Jayaram. March 2011.
- PEER 2011/02** *A Bayesian Network Methodology for Infrastructure Seismic Risk Assessment and Decision Support.* Michelle T. Bensi, Armen Der Kiureghian, and Daniel Straub. March 2011.
- PEER 2011/01** *Demand Fragility Surfaces for Bridges in Liquefied and Laterally Spreading Ground.* Scott J. Brandenberg, Jian Zhang, Pirooz Kashighandi, Yili Huo, and Minxing Zhao. March 2011.
- PEER 2010/05** *Guidelines for Performance-Based Seismic Design of Tall Buildings.* Developed by the Tall Buildings Initiative. November 2010.
- PEER 2010/04** *Application Guide for the Design of Flexible and Rigid Bus Connections between Substation Equipment Subjected to Earthquakes.* Jean-Bernard Dastous and Armen Der Kiureghian. September 2010.
- PEER 2010/03** *Shear Wave Velocity as a Statistical Function of Standard Penetration Test Resistance and Vertical Effective Stress at Caltrans Bridge Sites.* Scott J. Brandenberg, Naresh Bellana, and Thomas Shantz. June 2010.
- PEER 2010/02** *Stochastic Modeling and Simulation of Ground Motions for Performance-Based Earthquake Engineering.* Sanaz Rezaeian and Armen Der Kiureghian. June 2010.
- PEER 2010/01** *Structural Response and Cost Characterization of Bridge Construction Using Seismic Performance Enhancement Strategies.* Ady Aviram, Božidar Stojadinović, Gustavo J. Parra-Montesinos, and Kevin R. Mackie. March 2010.
- PEER 2009/03** *The Integration of Experimental and Simulation Data in the Study of Reinforced Concrete Bridge Systems Including Soil-Foundation-Structure Interaction.* Matthew Dryden and Gregory L. Fenves. November 2009.
- PEER 2009/02** *Improving Earthquake Mitigation through Innovations and Applications in Seismic Science, Engineering, Communication, and Response. Proceedings of a U.S.-Iran Seismic Workshop.* October 2009.
- PEER 2009/01** *Evaluation of Ground Motion Selection and Modification Methods: Predicting Median Interstory Drift Response of Buildings.* Curt B. Haselton, Ed. June 2009.
- PEER 2008/10** *Technical Manual for Strata.* Albert R. Kottke and Ellen M. Rathje. February 2009.
- PEER 2008/09** *NGA Model for Average Horizontal Component of Peak Ground Motion and Response Spectra.* Brian S.-J. Chiou and Robert R. Youngs. November 2008.
- PEER 2008/08** *Toward Earthquake-Resistant Design of Concentrically Braced Steel Structures.* Patxi Uriz and Stephen A. Mahin. November 2008.
- PEER 2008/07** *Using OpenSees for Performance-Based Evaluation of Bridges on Liquefiable Soils.* Stephen L. Kramer, Pedro Arduino, and HyungSuk Shin. November 2008.
- PEER 2008/06** *Shaking Table Tests and Numerical Investigation of Self-Centering Reinforced Concrete Bridge Columns.* Hyung IL Jeong, Junichi Sakai, and Stephen A. Mahin. September 2008.

- PEER 2008/05** *Performance-Based Earthquake Engineering Design Evaluation Procedure for Bridge Foundations Undergoing Liquefaction-Induced Lateral Ground Displacement.* Christian A. Ledezma and Jonathan D. Bray. August 2008.
- PEER 2008/04** *Benchmarking of Nonlinear Geotechnical Ground Response Analysis Procedures.* Jonathan P. Stewart, Annie On-Lei Kwok, Youssef M. A. Hashash, Neven Matasovic, Robert Pyke, Zhiliang Wang, and Zhaohui Yang. August 2008.
- PEER 2008/03** *Guidelines for Nonlinear Analysis of Bridge Structures in California.* Ady Aviram, Kevin R. Mackie, and Božidar Stojadinović. August 2008.
- PEER 2008/02** *Treatment of Uncertainties in Seismic-Risk Analysis of Transportation Systems.* Evangelos Stergiou and Anne S. Kiremidjian. July 2008.
- PEER 2008/01** *Seismic Performance Objectives for Tall Buildings.* William T. Holmes, Charles Kircher, William Petak, and Nabih Youssef. August 2008.
- PEER 2007/12** *An Assessment to Benchmark the Seismic Performance of a Code-Conforming Reinforced Concrete Moment-Frame Building.* Curt Haselton, Christine A. Goulet, Judith Mitrani-Reiser, James L. Beck, Gregory G. Deierlein, Keith A. Porter, Jonathan P. Stewart, and Ertugrul Taciroglu. August 2008.
- PEER 2007/11** *Bar Buckling in Reinforced Concrete Bridge Columns.* Wayne A. Brown, Dawn E. Lehman, and John F. Stanton. February 2008.
- PEER 2007/10** *Computational Modeling of Progressive Collapse in Reinforced Concrete Frame Structures.* Mohamed M. Talaat and Khalid M. Mosalam. May 2008.
- PEER 2007/09** *Integrated Probabilistic Performance-Based Evaluation of Benchmark Reinforced Concrete Bridges.* Kevin R. Mackie, John-Michael Wong, and Božidar Stojadinović. January 2008.
- PEER 2007/08** *Assessing Seismic Collapse Safety of Modern Reinforced Concrete Moment-Frame Buildings.* Curt B. Haselton and Gregory G. Deierlein. February 2008.
- PEER 2007/07** *Performance Modeling Strategies for Modern Reinforced Concrete Bridge Columns.* Michael P. Berry and Marc O. Eberhard. April 2008.
- PEER 2007/06** *Development of Improved Procedures for Seismic Design of Buried and Partially Buried Structures.* Linda Al Atik and Nicholas Sitar. June 2007.
- PEER 2007/05** *Uncertainty and Correlation in Seismic Risk Assessment of Transportation Systems.* Renee G. Lee and Anne S. Kiremidjian. July 2007.
- PEER 2007/04** *Numerical Models for Analysis and Performance-Based Design of Shallow Foundations Subjected to Seismic Loading.* Sivapalan Gajan, Tara C. Hutchinson, Bruce L. Kutter, Prishati Raychowdhury, José A. Ugalde, and Jonathan P. Stewart. May 2008.
- PEER 2007/03** *Beam-Column Element Model Calibrated for Predicting Flexural Response Leading to Global Collapse of RC Frame Buildings.* Curt B. Haselton, Abbie B. Liel, Sarah Taylor Lange, and Gregory G. Deierlein. May 2008.
- PEER 2007/02** *Campbell-Bozorgnia NGA Ground Motion Relations for the Geometric Mean Horizontal Component of Peak and Spectral Ground Motion Parameters.* Kenneth W. Campbell and Yousef Bozorgnia. May 2007.
- PEER 2007/01** *Boore-Atkinson NGA Ground Motion Relations for the Geometric Mean Horizontal Component of Peak and Spectral Ground Motion Parameters.* David M. Boore and Gail M. Atkinson. May. May 2007.
- PEER 2006/12** *Societal Implications of Performance-Based Earthquake Engineering.* Peter J. May. May 2007.
- PEER 2006/11** *Probabilistic Seismic Demand Analysis Using Advanced Ground Motion Intensity Measures, Attenuation Relationships, and Near-Fault Effects.* Polsak Tothong and C. Allin Cornell. March 2007.
- PEER 2006/10** *Application of the PEER PBEE Methodology to the I-880 Viaduct.* Sashi Kunnath. February 2007.
- PEER 2006/09** *Quantifying Economic Losses from Travel Forgone Following a Large Metropolitan Earthquake.* James Moore, Sungbin Cho, Yue Yue Fan, and Stuart Werner. November 2006.
- PEER 2006/08** *Vector-Valued Ground Motion Intensity Measures for Probabilistic Seismic Demand Analysis.* Jack W. Baker and C. Allin Cornell. October 2006.
- PEER 2006/07** *Analytical Modeling of Reinforced Concrete Walls for Predicting Flexural and Coupled-Shear-Flexural Responses.* Kutay Orakcal, Leonardo M. Massone, and John W. Wallace. October 2006.
- PEER 2006/06** *Nonlinear Analysis of a Soil-Drilled Pier System under Static and Dynamic Axial Loading.* Gang Wang and Nicholas Sitar. November 2006.
- PEER 2006/05** *Advanced Seismic Assessment Guidelines.* Paolo Bazzurro, C. Allin Cornell, Charles Menun, Maziar Motahari, and Nicolas Luco. September 2006.

- PEER 2006/04** *Probabilistic Seismic Evaluation of Reinforced Concrete Structural Components and Systems.* Tae Hyung Lee and Khalid M. Mosalam. August 2006.
- PEER 2006/03** *Performance of Lifelines Subjected to Lateral Spreading.* Scott A. Ashford and Teerawut Juirnarongrit. July 2006.
- PEER 2006/02** *Pacific Earthquake Engineering Research Center Highway Demonstration Project.* Anne Kiremidjian, James Moore, Yue Yue Fan, Nesrin Basoz, Ozgur Yazali, and Meredith Williams. April 2006.
- PEER 2006/01** *Bracing Berkeley. A Guide to Seismic Safety on the UC Berkeley Campus.* Mary C. Comerio, Stephen Tobriner, and Ariane Fehrenkamp. January 2006.
- PEER 2005/16** *Seismic Response and Reliability of Electrical Substation Equipment and Systems.* Junho Song, Armen Der Kiureghian, and Jerome L. Sackman. April 2006.
- PEER 2005/15** *CPT-Based Probabilistic Assessment of Seismic Soil Liquefaction Initiation.* R. E. S. Moss, R. B. Seed, R. E. Kayen, J. P. Stewart, and A. Der Kiureghian. April 2006.
- PEER 2005/14** *Workshop on Modeling of Nonlinear Cyclic Load-Deformation Behavior of Shallow Foundations.* Bruce L. Kutter, Geoffrey Martin, Tara Hutchinson, Chad Harden, Sivapalan Gajan, and Justin Phalen. March 2006.
- PEER 2005/13** *Stochastic Characterization and Decision Bases under Time-Dependent Aftershock Risk in Performance-Based Earthquake Engineering.* Gee Liek Yeo and C. Allin Cornell. July 2005.
- PEER 2005/12** *PEER Testbed Study on a Laboratory Building: Exercising Seismic Performance Assessment.* Mary C. Comerio, editor. November 2005.
- PEER 2005/11** *Van Nuys Hotel Building Testbed Report: Exercising Seismic Performance Assessment.* Helmut Krawinkler, editor. October 2005.
- PEER 2005/10** *First NEES/E-Defense Workshop on Collapse Simulation of Reinforced Concrete Building Structures.* September 2005.
- PEER 2005/09** *Test Applications of Advanced Seismic Assessment Guidelines.* Joe Maffei, Karl Telleen, Danya Mohr, William Holmes, and Yuki Nakayama. August 2006.
- PEER 2005/08** *Damage Accumulation in Lightly Confined Reinforced Concrete Bridge Columns.* R. Tyler Ranf, Jared M. Nelson, Zach Price, Marc O. Eberhard, and John F. Stanton. April 2006.
- PEER 2005/07** *Experimental and Analytical Studies on the Seismic Response of Freestanding and Anchored Laboratory Equipment.* Dimitrios Konstantinidis and Nicos Makris. January 2005.
- PEER 2005/06** *Global Collapse of Frame Structures under Seismic Excitations.* Luis F. Ibarra and Helmut Krawinkler. September 2005.
- PEER 2005/05** *Performance Characterization of Bench- and Shelf-Mounted Equipment.* Samit Ray Chaudhuri and Tara C. Hutchinson. May 2006.
- PEER 2005/04** *Numerical Modeling of the Nonlinear Cyclic Response of Shallow Foundations.* Chad Harden, Tara Hutchinson, Geoffrey R. Martin, and Bruce L. Kutter. August 2005.
- PEER 2005/03** *A Taxonomy of Building Components for Performance-Based Earthquake Engineering.* Keith A. Porter. September 2005.
- PEER 2005/02** *Fragility Basis for California Highway Overpass Bridge Seismic Decision Making.* Kevin R. Mackie and Božidar Stojadinović. June 2005.
- PEER 2005/01** *Empirical Characterization of Site Conditions on Strong Ground Motion.* Jonathan P. Stewart, Yoojoong Choi, and Robert W. Graves. June 2005.
- PEER 2004/09** *Electrical Substation Equipment Interaction: Experimental Rigid Conductor Studies.* Christopher Stearns and André Filiatrault. February 2005.
- PEER 2004/08** *Seismic Qualification and Fragility Testing of Line Break 550-kV Disconnect Switches.* Shakhzod M. Takhirov, Gregory L. Fenves, and Eric Fujisaki. January 2005.
- PEER 2004/07** *Ground Motions for Earthquake Simulator Qualification of Electrical Substation Equipment.* Shakhzod M. Takhirov, Gregory L. Fenves, Eric Fujisaki, and Don Clyde. January 2005.
- PEER 2004/06** *Performance-Based Regulation and Regulatory Regimes.* Peter J. May and Chris Koski. September 2004.
- PEER 2004/05** *Performance-Based Seismic Design Concepts and Implementation: Proceedings of an International Workshop.* Peter Fajfar and Helmut Krawinkler, editors. September 2004.
- PEER 2004/04** *Seismic Performance of an Instrumented Tilt-up Wall Building.* James C. Anderson and Vitelmo V. Bertero. July 2004.

- PEER 2004/03** *Evaluation and Application of Concrete Tilt-up Assessment Methodologies.* Timothy Graf and James O. Malley. October 2004.
- PEER 2004/02** *Analytical Investigations of New Methods for Reducing Residual Displacements of Reinforced Concrete Bridge Columns.* Junichi Sakai and Stephen A. Mahin. August 2004.
- PEER 2004/01** *Seismic Performance of Masonry Buildings and Design Implications.* Kerri Anne Taeko Tokoro, James C. Anderson, and Vitelmo V. Bertero. February 2004.
- PEER 2003/18** *Performance Models for Flexural Damage in Reinforced Concrete Columns.* Michael Berry and Marc Eberhard. August 2003.
- PEER 2003/17** *Predicting Earthquake Damage in Older Reinforced Concrete Beam-Column Joints.* Catherine Pagni and Laura Lowes. October 2004.
- PEER 2003/16** *Seismic Demands for Performance-Based Design of Bridges.* Kevin Mackie and Božidar Stojadinović. August 2003.
- PEER 2003/15** *Seismic Demands for Nondeteriorating Frame Structures and Their Dependence on Ground Motions.* Ricardo Antonio Medina and Helmut Krawinkler. May 2004.
- PEER 2003/14** *Finite Element Reliability and Sensitivity Methods for Performance-Based Earthquake Engineering.* Terje Haukaas and Armen Der Kiureghian. April 2004.
- PEER 2003/13** *Effects of Connection Hysteretic Degradation on the Seismic Behavior of Steel Moment-Resisting Frames.* Janise E. Rodgers and Stephen A. Mahin. March 2004.
- PEER 2003/12** *Implementation Manual for the Seismic Protection of Laboratory Contents: Format and Case Studies.* William T. Holmes and Mary C. Comerio. October 2003.
- PEER 2003/11** *Fifth U.S.-Japan Workshop on Performance-Based Earthquake Engineering Methodology for Reinforced Concrete Building Structures.* February 2004.
- PEER 2003/10** *A Beam-Column Joint Model for Simulating the Earthquake Response of Reinforced Concrete Frames.* Laura N. Lowes, Nilanjan Mitra, and Arash Altoontash. February 2004.
- PEER 2003/09** *Sequencing Repairs after an Earthquake: An Economic Approach.* Marco Casari and Simon J. Wilkie. April 2004.
- PEER 2003/08** *A Technical Framework for Probability-Based Demand and Capacity Factor Design (DCFD) Seismic Formats.* Fatemeh Jalayer and C. Allin Cornell. November 2003.
- PEER 2003/07** *Uncertainty Specification and Propagation for Loss Estimation Using FOSM Methods.* Jack W. Baker and C. Allin Cornell. September 2003.
- PEER 2003/06** *Performance of Circular Reinforced Concrete Bridge Columns under Bidirectional Earthquake Loading.* Mahmoud M. Hachem, Stephen A. Mahin, and Jack P. Moehle. February 2003.
- PEER 2003/05** *Response Assessment for Building-Specific Loss Estimation.* Eduardo Miranda and Shahram Taghavi. September 2003.
- PEER 2003/04** *Experimental Assessment of Columns with Short Lap Splices Subjected to Cyclic Loads.* Murat Melek, John W. Wallace, and Joel Conte. April 2003.
- PEER 2003/03** *Probabilistic Response Assessment for Building-Specific Loss Estimation.* Eduardo Miranda and Hesameddin Aslani. September 2003.
- PEER 2003/02** *Software Framework for Collaborative Development of Nonlinear Dynamic Analysis Program.* Jun Peng and Kincho H. Law. September 2003.
- PEER 2003/01** *Shake Table Tests and Analytical Studies on the Gravity Load Collapse of Reinforced Concrete Frames.* Kenneth John Elwood and Jack P. Moehle. November 2003.
- PEER 2002/24** *Performance of Beam to Column Bridge Joints Subjected to a Large Velocity Pulse.* Natalie Gibson, André Filiatrault, and Scott A. Ashford. April 2002.
- PEER 2002/23** *Effects of Large Velocity Pulses on Reinforced Concrete Bridge Columns.* Greg L. Orozco and Scott A. Ashford. April 2002.
- PEER 2002/22** *Characterization of Large Velocity Pulses for Laboratory Testing.* Kenneth E. Cox and Scott A. Ashford. April 2002.
- PEER 2002/21** *Fourth U.S.-Japan Workshop on Performance-Based Earthquake Engineering Methodology for Reinforced Concrete Building Structures.* December 2002.
- PEER 2002/20** *Barriers to Adoption and Implementation of PBEE Innovations.* Peter J. May. August 2002.

- PEER 2002/19** *Economic-Engineered Integrated Models for Earthquakes: Socioeconomic Impacts.* Peter Gordon, James E. Moore II, and Harry W. Richardson. July 2002.
- PEER 2002/18** *Assessment of Reinforced Concrete Building Exterior Joints with Substandard Details.* Chris P. Pantelides, Jon Hansen, Justin Nadauld, and Lawrence D. Reaveley. May 2002.
- PEER 2002/17** *Structural Characterization and Seismic Response Analysis of a Highway Overcrossing Equipped with Elastomeric Bearings and Fluid Dampers: A Case Study.* Nicos Makris and Jian Zhang. November 2002.
- PEER 2002/16** *Estimation of Uncertainty in Geotechnical Properties for Performance-Based Earthquake Engineering.* Allen L. Jones, Steven L. Kramer, and Pedro Arduino. December 2002.
- PEER 2002/15** *Seismic Behavior of Bridge Columns Subjected to Various Loading Patterns.* Asadollah Esmaeily-Gh. and Yan Xiao. December 2002.
- PEER 2002/14** *Inelastic Seismic Response of Extended Pile Shaft Supported Bridge Structures.* T.C. Hutchinson, R.W. Boulanger, Y.H. Chai, and I.M. Idriss. December 2002.
- PEER 2002/13** *Probabilistic Models and Fragility Estimates for Bridge Components and Systems.* Paolo Gardoni, Armen Der Kiureghian, and Khalid M. Mosalam. June 2002.
- PEER 2002/12** *Effects of Fault Dip and Slip Rake on Near-Source Ground Motions: Why Chi-Chi Was a Relatively Mild M7.6 Earthquake.* Brad T. Aagaard, John F. Hall, and Thomas H. Heaton. December 2002.
- PEER 2002/11** *Analytical and Experimental Study of Fiber-Reinforced Strip Isolators.* James M. Kelly and Shakhzod M. Takhirov. September 2002.
- PEER 2002/10** *Centrifuge Modeling of Settlement and Lateral Spreading with Comparisons to Numerical Analyses.* Sivapalan Gajan and Bruce L. Kutter. January 2003.
- PEER 2002/09** *Documentation and Analysis of Field Case Histories of Seismic Compression during the 1994 Northridge, California, Earthquake.* Jonathan P. Stewart, Patrick M. Smith, Daniel H. Whang, and Jonathan D. Bray. October 2002.
- PEER 2002/08** *Component Testing, Stability Analysis and Characterization of Buckling-Restrained Unbonded BracesTM.* Cameron Black, Nicos Makris, and Ian Aiken. September 2002.
- PEER 2002/07** *Seismic Performance of Pile-Wharf Connections.* Charles W. Roeder, Robert Graff, Jennifer Soderstrom, and Jun Han Yoo. December 2001.
- PEER 2002/06** *The Use of Benefit-Cost Analysis for Evaluation of Performance-Based Earthquake Engineering Decisions.* Richard O. Zerbe and Anthony Falit-Baiamonte. September 2001.
- PEER 2002/05** *Guidelines, Specifications, and Seismic Performance Characterization of Nonstructural Building Components and Equipment.* André Filiatrault, Constantin Christopoulos, and Christopher Stearns. September 2001.
- PEER 2002/04** *Consortium of Organizations for Strong-Motion Observation Systems and the Pacific Earthquake Engineering Research Center Lifelines Program: Invited Workshop on Archiving and Web Dissemination of Geotechnical Data, 4–5 October 2001.* September 2002.
- PEER 2002/03** *Investigation of Sensitivity of Building Loss Estimates to Major Uncertain Variables for the Van Nuys Testbed.* Keith A. Porter, James L. Beck, and Rustem V. Shaikhutdinov. August 2002.
- PEER 2002/02** *The Third U.S.-Japan Workshop on Performance-Based Earthquake Engineering Methodology for Reinforced Concrete Building Structures.* July 2002.
- PEER 2002/01** *Nonstructural Loss Estimation: The UC Berkeley Case Study.* Mary C. Comerio and John C. Stallmeyer. December 2001.
- PEER 2001/16** *Statistics of SDF-System Estimate of Roof Displacement for Pushover Analysis of Buildings.* Anil K. Chopra, Rakesh K. Goel, and Chatpan Chintanapakdee. December 2001.
- PEER 2001/15** *Damage to Bridges during the 2001 Nisqually Earthquake.* R. Tyler Ranf, Marc O. Eberhard, and Michael P. Berry. November 2001.
- PEER 2001/14** *Rocking Response of Equipment Anchored to a Base Foundation.* Nicos Makris and Cameron J. Black. September 2001.
- PEER 2001/13** *Modeling Soil Liquefaction Hazards for Performance-Based Earthquake Engineering.* Steven L. Kramer and Ahmed-W. Elgamel. February 2001.
- PEER 2001/12** *Development of Geotechnical Capabilities in OpenSees.* Boris Jeremić. September 2001.
- PEER 2001/11** *Analytical and Experimental Study of Fiber-Reinforced Elastomeric Isolators.* James M. Kelly and Shakhzod M. Takhirov. September 2001.

- PEER 2001/10** *Amplification Factors for Spectral Acceleration in Active Regions.* Jonathan P. Stewart, Andrew H. Liu, Yoojoong Choi, and Mehmet B. Baturay. December 2001.
- PEER 2001/09** *Ground Motion Evaluation Procedures for Performance-Based Design.* Jonathan P. Stewart, Shyh-Jeng Chiou, Jonathan D. Bray, Robert W. Graves, Paul G. Somerville, and Norman A. Abrahamson. September 2001.
- PEER 2001/08** *Experimental and Computational Evaluation of Reinforced Concrete Bridge Beam-Column Connections for Seismic Performance.* Clay J. Naito, Jack P. Moehle, and Khalid M. Mosalam. November 2001.
- PEER 2001/07** *The Rocking Spectrum and the Shortcomings of Design Guidelines.* Nicos Makris and Dimitrios Konstantinidis. August 2001.
- PEER 2001/06** *Development of an Electrical Substation Equipment Performance Database for Evaluation of Equipment Fragilities.* Thalia Agnanos. April 1999.
- PEER 2001/05** *Stiffness Analysis of Fiber-Reinforced Elastomeric Isolators.* Hsiang-Chuan Tsai and James M. Kelly. May 2001.
- PEER 2001/04** *Organizational and Societal Considerations for Performance-Based Earthquake Engineering.* Peter J. May. April 2001.
- PEER 2001/03** *A Modal Pushover Analysis Procedure to Estimate Seismic Demands for Buildings: Theory and Preliminary Evaluation.* Anil K. Chopra and Rakesh K. Goel. January 2001.
- PEER 2001/02** *Seismic Response Analysis of Highway Overcrossings Including Soil-Structure Interaction.* Jian Zhang and Nicos Makris. March 2001.
- PEER 2001/01** *Experimental Study of Large Seismic Steel Beam-to-Column Connections.* Egor P. Popov and Shakhzod M. Takhirov. November 2000.
- PEER 2000/10** *The Second U.S.-Japan Workshop on Performance-Based Earthquake Engineering Methodology for Reinforced Concrete Building Structures.* March 2000.
- PEER 2000/09** *Structural Engineering Reconnaissance of the August 17, 1999 Earthquake: Kocaeli (Izmit), Turkey.* Halil Sezen, Kenneth J. Elwood, Andrew S. Whittaker, Khalid Mosalam, John J. Wallace, and John F. Stanton. December 2000.
- PEER 2000/08** *Behavior of Reinforced Concrete Bridge Columns Having Varying Aspect Ratios and Varying Lengths of Confinement.* Anthony J. Calderone, Dawn E. Lehman, and Jack P. Moehle. January 2001.
- PEER 2000/07** *Cover-Plate and Flange-Plate Reinforced Steel Moment-Resisting Connections.* Taejin Kim, Andrew S. Whittaker, Amir S. Gilani, Vitelmo V. Bertero, and Shakhzod M. Takhirov. September 2000.
- PEER 2000/06** *Seismic Evaluation and Analysis of 230-kV Disconnect Switches.* Amir S. J. Gilani, Andrew S. Whittaker, Gregory L. Fenves, Chun-Hao Chen, Henry Ho, and Eric Fujisaki. July 2000.
- PEER 2000/05** *Performance-Based Evaluation of Exterior Reinforced Concrete Building Joints for Seismic Excitation.* Chandra Clyde, Chris P. Pantelides, and Lawrence D. Reaveley. July 2000.
- PEER 2000/04** *An Evaluation of Seismic Energy Demand: An Attenuation Approach.* Chung-Che Chou and Chia-Ming Uang. July 1999.
- PEER 2000/03** *Framing Earthquake Retrofitting Decisions: The Case of Hillside Homes in Los Angeles.* Detlof von Winterfeldt, Nels Roselund, and Alicia Kitsuse. March 2000.
- PEER 2000/02** *U.S.-Japan Workshop on the Effects of Near-Field Earthquake Shaking.* Andrew Whittaker, ed. July 2000.
- PEER 2000/01** *Further Studies on Seismic Interaction in Interconnected Electrical Substation Equipment.* Armen Der Kiureghian, Kee-Jeung Hong, and Jerome L. Sackman. November 1999.
- PEER 1999/14** *Seismic Evaluation and Retrofit of 230-kV Porcelain Transformer Bushings.* Amir S. Gilani, Andrew S. Whittaker, Gregory L. Fenves, and Eric Fujisaki. December 1999.
- PEER 1999/13** *Building Vulnerability Studies: Modeling and Evaluation of Tilt-up and Steel Reinforced Concrete Buildings.* John W. Wallace, Jonathan P. Stewart, and Andrew S. Whittaker, editors. December 1999.
- PEER 1999/12** *Rehabilitation of Nonductile RC Frame Building Using Encasement Plates and Energy-Dissipating Devices.* Mehrdad Sasani, Vitelmo V. Bertero, James C. Anderson. December 1999.
- PEER 1999/11** *Performance Evaluation Database for Concrete Bridge Components and Systems under Simulated Seismic Loads.* Yael D. Hose and Frieder Seible. November 1999.
- PEER 1999/10** *U.S.-Japan Workshop on Performance-Based Earthquake Engineering Methodology for Reinforced Concrete Building Structures.* December 1999.
- PEER 1999/09** *Performance Improvement of Long Period Building Structures Subjected to Severe Pulse-Type Ground Motions.* James C. Anderson, Vitelmo V. Bertero, and Raul Bertero. October 1999.

- PEER 1999/08** *Envelopes for Seismic Response Vectors.* Charles Menun and Armen Der Kiureghian. July 1999.
- PEER 1999/07** *Documentation of Strengths and Weaknesses of Current Computer Analysis Methods for Seismic Performance of Reinforced Concrete Members.* William F. Cofer. November 1999.
- PEER 1999/06** *Rocking Response and Overturning of Anchored Equipment under Seismic Excitations.* Nicos Makris and Jian Zhang. November 1999.
- PEER 1999/05** *Seismic Evaluation of 550 kV Porcelain Transformer Bushings.* Amir S. Gilani, Andrew S. Whittaker, Gregory L. Fenves, and Eric Fujisaki. October 1999.
- PEER 1999/04** *Adoption and Enforcement of Earthquake Risk-Reduction Measures.* Peter J. May, Raymond J. Burby, T. Jens Feeley, and Robert Wood.
- PEER 1999/03** *Task 3 Characterization of Site Response General Site Categories.* Adrian Rodriguez-Marek, Jonathan D. Bray, and Norman Abrahamson. February 1999.
- PEER 1999/02** *Capacity-Demand-Diagram Methods for Estimating Seismic Deformation of Inelastic Structures: SDF Systems.* Anil K. Chopra and Rakesh Goel. April 1999.
- PEER 1999/01** *Interaction in Interconnected Electrical Substation Equipment Subjected to Earthquake Ground Motions.* Armen Der Kiureghian, Jerome L. Sackman, and Kee-Jeung Hong. February 1999.
- PEER 1998/08** *Behavior and Failure Analysis of a Multiple-Frame Highway Bridge in the 1994 Northridge Earthquake.* Gregory L. Fenves and Michael Ellery. December 1998.
- PEER 1998/07** *Empirical Evaluation of Inertial Soil-Structure Interaction Effects.* Jonathan P. Stewart, Raymond B. Seed, and Gregory L. Fenves. November 1998.
- PEER 1998/06** *Effect of Damping Mechanisms on the Response of Seismic Isolated Structures.* Nicos Makris and Shih-Po Chang. November 1998.
- PEER 1998/05** *Rocking Response and Overturning of Equipment under Horizontal Pulse-Type Motions.* Nicos Makris and Yiannis Roussos. October 1998.
- PEER 1998/04** *Pacific Earthquake Engineering Research Invitational Workshop Proceedings, May 14–15, 1998: Defining the Links between Planning, Policy Analysis, Economics and Earthquake Engineering.* Mary Comerio and Peter Gordon. September 1998.
- PEER 1998/03** *Repair/Upgrade Procedures for Welded Beam to Column Connections.* James C. Anderson and Xiaojing Duan. May 1998.
- PEER 1998/02** *Seismic Evaluation of 196 kV Porcelain Transformer Bushings.* Amir S. Gilani, Juan W. Chavez, Gregory L. Fenves, and Andrew S. Whittaker. May 1998.
- PEER 1998/01** *Seismic Performance of Well-Confined Concrete Bridge Columns.* Dawn E. Lehman and Jack P. Moehle. December 2000.

ONLINE PEER REPORTS

The following PEER reports are available by Internet only at http://peer.berkeley.edu/publications/peer_reports_complete.html.

- PEER 2012/103** *Performance-Based Seismic Demand Assessment of Concentrically Braced Steel Frame Buildings*. Chui-Hsin Chen and Stephen A. Mahin. December 2012.
- PEER 2012/102** *Procedure to Restart an Interrupted Hybrid Simulation: Addendum to PEER Report 2010/103*. Vesna Terzic and Božidar Stojadinovic. October 2012.
- PEER 2012/101** *Mechanics of Fiber Reinforced Bearings*. James M. Kelly and Andrea Calabrese. February 2012.
- PEER 2011/107** *Nonlinear Site Response and Seismic Compression at Vertical Array Strongly Shaken by 2007 Niigata-ken Chuetsu-oki Earthquake*. Eric Yee, Jonathan P. Stewart, and Kohji Tokimatsu. December 2011.
- PEER 2011/106** *Self Compacting Hybrid Fiber Reinforced Concrete Composites for Bridge Columns*. Pardeep Kumar, Gabriel Jen, William Trono, Marios Panagiotou, and Claudia Ostertag. September 2011.
- PEER 2011/105** *Stochastic Dynamic Analysis of Bridges Subjected to Spatially Varying Ground Motions*. Katerina Konakli and Armen Der Kiureghian. August 2011.
- PEER 2011/104** *Design and Instrumentation of the 2010 E-Defense Four-Story Reinforced Concrete and Post-Tensioned Concrete Buildings*. Takuya Nagae, Kenichi Tahara, Taizo Matsumori, Hitoshi Shiohara, Toshimi Kabeyasawa, Susumu Kono, Minehiro Nishiyama (Japanese Research Team) and John Wallace, Wassim Ghannoum, Jack Moehle, Richard Sause, Wesley Keller, Zeynep Tuna (U.S. Research Team). June 2011.
- PEER 2011/103** *In-Situ Monitoring of the Force Output of Fluid Dampers: Experimental Investigation*. Dimitrios Konstantinidis, James M. Kelly, and Nicos Makris. April 2011.
- PEER 2011/102** *Ground-motion prediction equations 1964 - 2010*. John Douglas. April 2011.
- PEER 2011/101** *Report of the Eighth Planning Meeting of NEES/E-Defense Collaborative Research on Earthquake Engineering*. Convened by the Hyogo Earthquake Engineering Research Center (NIED), NEES Consortium, Inc. February 2011.
- PEER 2010/111** *Modeling and Acceptance Criteria for Seismic Design and Analysis of Tall Buildings*. Task 7 Report for the Tall Buildings Initiative - Published jointly by the Applied Technology Council. October 2010.
- PEER 2010/110** *Seismic Performance Assessment and Probabilistic Repair Cost Analysis of Precast Concrete Cladding Systems for Multistory Buildings*. Jeffrey P. Hunt and Božidar Stojadinovic. November 2010.
- PEER 2010/109** *Report of the Seventh Joint Planning Meeting of NEES/E-Defense Collaboration on Earthquake Engineering. Held at the E-Defense, Miki, and Shin-Kobe, Japan, September 18–19, 2009*. August 2010.
- PEER 2010/108** *Probabilistic Tsunami Hazard in California*. Hong Kie Thio, Paul Somerville, and Jascha Polet, preparers. October 2010.
- PEER 2010/107** *Performance and Reliability of Exposed Column Base Plate Connections for Steel Moment-Resisting Frames*. Ady Aviram, Božidar Stojadinovic, and Armen Der Kiureghian. August 2010.
- PEER 2010/106** *Verification of Probabilistic Seismic Hazard Analysis Computer Programs*. Patricia Thomas, Ivan Wong, and Norman Abrahamson. May 2010.
- PEER 2010/105** *Structural Engineering Reconnaissance of the April 6, 2009, Abruzzo, Italy, Earthquake, and Lessons Learned*. M. Selim Güney and Khalid M. Mosalam. April 2010.
- PEER 2010/104** *Simulating the Inelastic Seismic Behavior of Steel Braced Frames, Including the Effects of Low-Cycle Fatigue*. Yuli Huang and Stephen A. Mahin. April 2010.
- PEER 2010/103** *Post-Earthquake Traffic Capacity of Modern Bridges in California*. Vesna Terzic and Božidar Stojadinović. March 2010.
- PEER 2010/102** *Analysis of Cumulative Absolute Velocity (CAV) and JMA Instrumental Seismic Intensity (I_{JMA}) Using the PEER–NGA Strong Motion Database*. Kenneth W. Campbell and Yousef Bozorgnia. February 2010.
- PEER 2010/101** *Rocking Response of Bridges on Shallow Foundations*. Jose A. Ugalde, Bruce L. Kutter, and Boris Jeremic. April 2010.
- PEER 2009/109** *Simulation and Performance-Based Earthquake Engineering Assessment of Self-Centering Post-Tensioned Concrete Bridge Systems*. Won K. Lee and Sarah L. Billington. December 2009.
- PEER 2009/108** *PEER Lifelines Geotechnical Virtual Data Center*. J. Carl Stepp, Daniel J. Ponti, Loren L. Turner, Jennifer N. Swift, Sean Devlin, Yang Zhu, Jean Benoit, and John Bobbitt. September 2009.
- PEER 2009/107** *Experimental and Computational Evaluation of Current and Innovative In-Span Hinge Details in Reinforced Concrete Box-Girder Bridges: Part 2: Post-Test Analysis and Design Recommendations*. Matias A. Hube and Khalid M. Mosalam. December 2009.

- PEER 2009/106** *Shear Strength Models of Exterior Beam-Column Joints without Transverse Reinforcement.* Sangjoon Park and Khalid M. Mosalam. November 2009.
- PEER 2009/105** *Reduced Uncertainty of Ground Motion Prediction Equations through Bayesian Variance Analysis.* Robb Eric S. Moss. November 2009.
- PEER 2009/104** *Advanced Implementation of Hybrid Simulation.* Andreas H. Schellenberg, Stephen A. Mahin, Gregory L. Fenves. November 2009.
- PEER 2009/103** *Performance Evaluation of Innovative Steel Braced Frames.* T. Y. Yang, Jack P. Moehle, and Božidar Stojadinovic. August 2009.
- PEER 2009/102** *Reinvestigation of Liquefaction and Nonliquefaction Case Histories from the 1976 Tangshan Earthquake.* Robb Eric Moss, Robert E. Kayen, Liyuan Tong, Songyu Liu, Guojun Cai, and Jiaer Wu. August 2009.
- PEER 2009/101** *Report of the First Joint Planning Meeting for the Second Phase of NEES/E-Defense Collaborative Research on Earthquake Engineering.* Stephen A. Mahin et al. July 2009.
- PEER 2008/104** *Experimental and Analytical Study of the Seismic Performance of Retaining Structures.* Linda Al Atik and Nicholas Sitar. January 2009.
- PEER 2008/103** *Experimental and Computational Evaluation of Current and Innovative In-Span Hinge Details in Reinforced Concrete Box-Girder Bridges. Part 1: Experimental Findings and Pre-Test Analysis.* Matias A. Hube and Khalid M. Mosalam. January 2009.
- PEER 2008/102** *Modeling of Unreinforced Masonry Infill Walls Considering In-Plane and Out-of-Plane Interaction.* Stephen Kadosiewicz and Khalid M. Mosalam. January 2009.
- PEER 2008/101** *Seismic Performance Objectives for Tall Buildings.* William T. Holmes, Charles Kircher, William Petak, and Nabih Youssef. August 2008.
- PEER 2007/101** *Generalized Hybrid Simulation Framework for Structural Systems Subjected to Seismic Loading.* Tarek Elkhoraibi and Khalid M. Mosalam. July 2007.
- PEER 2007/100** *Seismic Evaluation of Reinforced Concrete Buildings Including Effects of Masonry Infill Walls.* Alidad Hashemi and Khalid M. Mosalam. July 2007.

The Pacific Earthquake Engineering Research Center (PEER) is a multi-institutional research and education center with headquarters at the University of California, Berkeley. Investigators from over 20 universities, several consulting companies, and researchers at various state and federal government agencies contribute to research programs focused on performance-based earthquake engineering.

These research programs aim to identify and reduce the risks from major earthquakes to life safety and to the economy by including research in a wide variety of disciplines including structural and geotechnical engineering, geology/seismology, lifelines, transportation, architecture, economics, risk management, and public policy.

PEER is supported by federal, state, local, and regional agencies, together with industry partners.



PEER Core Institutions:

University of California, Berkeley (Lead Institution)
California Institute of Technology
Oregon State University
Stanford University
University of California, Davis
University of California, Irvine
University of California, Los Angeles
University of California, San Diego
University of Southern California
University of Washington

PEER reports can be ordered at http://peer.berkeley.edu/publications/peer_reports.html or by contacting

Pacific Earthquake Engineering Research Center
University of California, Berkeley
325 Davis Hall, mail code 1792
Berkeley, CA 94720-1792
Tel: 510-642-3437
Fax: 510-642-1655
Email: peer_editor@berkeley.edu

ISSN 1547-0587X